





#### **ADDRESS OF PUBLISHER** & EDITOR'S OFFICE:

## **GDAŃSK UNIVERSITY OF TECHNOLOGY** Faculty of Ocean Engineering 4 Guoming Chen, Junhua Hu, An Liu, Jinfu Feng, Qingqing Hu & Ship Technology MOTION CHARACTERISTICS AFTER RICOCHET: AN EXPERIMENTAL G. Narutowicza 11/12 INVESTIGATION 80-233 Gdańsk, POLAND Li Guangnian, Qingren Chen, Yue Liu 11

- EM FOR
  - ANOATE V-SPEED

	I WO-SIROKE	DIE	SEL ENGINE						
96	Shen Wu, Pan Zhang, Haijun Wei, Lei Chen								
	INFLUENCE	OF	SURFACE	TEXTURE	PARAMETERS	ON	FRICTION		

## **CONTENS**

,		0 , 0 ,
		EXPERIMENTAL STUDY ON DYNAMIC STRUCTURE OF PROPELLER TIP VORTEX
	19	Jin Zou, Guoge Tan, Hanbing Sun, Jie Xu, Yongkang Hou
		NUMERICAL SIMULATION OF THE DUCTED PROPELLER AND APPLICATION
		TO A SEMI-SUBMERGED VEHICLE
	30	Wenbin Lai, Detang Li, Yonghe Xie
EDITORIAL STAFF:		SIMULATION AND EXPERIMENTAL STUDY OF HYDRAULIC CYLINDER IN
		OSCILLATING FLOAT-TYPE WAVE ENERGY CONVERTER
Wiesław Tarełko	39	Karolina Jurczyk, Paweł Piskur, Piotr Szymak
Editor in Chief		PARAMETERS IDENTIFICATION OF THE FLEXIBLE FIN KINEMATICS MODEL
Janusz Kozak		USING VISION AND GENETIC ALGORITHMS
Deputy Editors-in-Chief	48	Guanghai Gao, Yunjing Cui, Xingqi Qiu
Wojciech Litwin		PREDICTION OF VORTEX-INDUCED VIBRATION RESPONSE OF DEEP SEA
Deputy Editors-in-Chief		TOP-TENSIONED RISER IN SHEARED FLOW CONSIDERING PARAMETRIC
		EXCITATIONS
	58	Vladimir S. Blintsov, Konstantin S. Trunin, Wiesław Tarełko
		DETERMINATION OF ADDITIONAL TENSION IN TOWED STREAMER CABLE
		TRIGGERED BY COLLISION WITH UNDERWATER MOVING OBJECT
Price:	69	Jan P. Michalski
single issue: 25 PLN		PARAMETRIC METHOD APPLICABLE IN ASSESSING BREAKOUT FORCE AND
C		TIME FOR LIFTING SLENDER BODIES FROM SEABED
Prices for abroad	76	Xiaoyong Gu, Guohe Jiang, Zhenghua Guo, Shangzhi Ding
single issue:		DESIGN AND EXPERIMENT OF LOW-PRESSURE GAS SUPPLY SYSTEM FOR
- in Europe EURO 15		DUAL FUEL ENGINE
- overseas USD 20	85	Shiye Wang, Li Yao
		EFFECT OF ENGINE SPEEDS AND DIMETHYL ETHER ON METHYL DECANOATE
WEB:		HCCI COMBUSTION AND EMISSION CHARACTERISTICS BASED ON LOW-SPEED
pg.edu.pl/pmr		TWO-STROKE DIESEL ENGINE
10 10 11	96	Shen Wu, Pan Zhang, Haijun Wei, Lei Chen
e-mail : pmr@pg edu pl		INFLUENCE OF SURFACE TEXTURE PARAMETERS ON FRICTION
e man i prine pgreaupi		CHARACTERISTICS UNDER STARVED LUBRICATION
ISSN 1233-2585		

#### ADDRESS OF PUBLISHER & EDITOR'S OFFICE:

#### GDAŃSK UNIVERSITY OF TECHNOLOGY

Faculty of Ocean Engineering & Ship Technology G. Narutowicza 11/12 80-233 Gdańsk, POLAND

- 107 Tomasz Kwaśniewski, Marian Piwowarski DESIGN ANALYSIS OF HYBRID GAS TURBINE-FUEL CELL POWER PLANT IN STATIONARY AND MARINE APPLICATIONS 120 Zbigniew Korczewski, Konrad Marszałkowski ENERGY ANALYSIS OF THE PROPULSION SHAFT FATIGUE PROCESS IN A ROTATING MECHANICAL SYSTEM PART II IDENTIFICATION STUDIES - DEVELOPING THE FATIGUE DURABILITY MODEL OF A DRIVE SHAFT 125 Paweł Śliwiński THE INFLUENCE OF WATER AND MINERAL OIL ON MECHANICAL LOSSES IN A HYDRAULIC MOTOR FOR OFFSHORE AND MARINE APPLICATIONS Jerzy Girtler 136 LIMITING DISTRIBUTION OF THE THREE-STATE SEMI-MARKOV MODEL OF TECHNICAL STATE TRANSITIONS OF SHIP POWER PLANT MACHINES AND ITS APPLICABILITY IN OPERATIONAL DECISION-MAKING 145 Xiaowen Li, Zhaoyi Zhu, Yan Li, Zhe Hu DESIGN AND MECHANICAL ANALYSIS OF A COMPOSITE T-TYPE CONNECTION STRUCTURE FOR MARINE STRUCTURES Tomasz Ferenc, Tomasz Mikulski 158 VALIDATION PROCESS FOR COMPUTATIONAL MODEL OF FULL-SCALE SEGMENT FOR DESIGN OF COMPOSITE FOOTBRIDGE 168 Krystian Buszman, Małgorzata Gloza DETECTION OF FLOATING OBJECTS BASED ON HYDROACOUSTIC AND HYDRODYNAMIC PRESSURE MEASUREMENTS IN THE COASTAL ZONE 176 **Ryszard Kłos** ULTRASONIC DETECTION OF THE INTRAVASCULAR FREE GAS PHASE IN RESEARCH ON DIVING 187 Yang Ju, Zhengxian Wei, Li Huangfu, Feng Xiao
  - A NEW LOW SNR UNDERWATER ACOUSTIC SIGNAL CLASSIFICATION METHOD BASED ON INTRINSIC MODAL FEATURES MAINTAINING DIMENSIONALITY REDUCTION

#### Editorial

POLISH MARITIME RESEARCH is the scientific journal with a worldwide circulation. This journal is published quarterly (four times a year) by Gdansk University of Technology (GUT). On September, 1994, the first issue of POLISH MARITIME RESEARCH was published. The main objective of this journal is to present original research, innovative scientific ideas, and significant findings and application in the field of :

#### Naval Architecture, Ocean Engineering and Underwater Technology,

The scope of the journal covers selected issues related to all phases of product lifecycle and corresponding technologies for offshore floating and fixed structures and their components.

All researchers are invited to submit their original papers for peer review and publications related to methods of the design; production and manufacturing; maintenance and operational processes of such technical items as:

- all types of vessels and their equipment,
- fixed and floating offshore units and their components,
- autonomous underwater vehicle (AUV) and remotely operated vehicle (ROV).
- We welcome submissions from these fields in the following technical topics:
  - ship hydrodynamics: buoyancy and stability; ship resistance and propulsion, etc.,
  - structural integrity of ship and offshore unit structures: materials; welding; fatigue and fracture, etc.,
  - marine equipment: ship and offshore unit power plants: overboarding equipment; etc.

#### **Scientific Board**

Chairman : Prof. JERZY GIRTLER - Gdańsk University of Technology, Poland Vice-chairman : Prof. CARLOS GUEDES SOARES, Universidade de Lisboa, Lisbon, Portugal Vice-chairman : Prof. MIROSŁAW L. WYSZYŃSKI - University of Birmingham, United Kingdom

Prof. POUL ANDERSEN Technical University of Denmark Kongens Lyngby Denmark

Prof. JIAHN-HORNG CHEN National Taiwan Ocean University Keelung Taiwan

> Prof. VINCENZO CRUPI University of Messina Messina Italy

Prof. MAREK DZIDA Gdansk University of Technology Gdansk Poland

Prof. ODD MAGNUS FALTINSEN Norwegian University of Science and Technology Trondheim Norway

> Prof. MASSIMO FIGARI University of Genova Genova Italy

Prof. HASSAN GHASSEMI Amirkabir University of Technology Tehran Iran Prof. STOJCE DIMOV ILCEV Durban University of Technology Durban South Africa

Prof. YORDAN GARBATOV Universidade de Lisboa, Lisbon Portugal

Prof. STANISLAW GUCMA Maritime University of Szczecin Szczecin Poland

Prof. ANTONI ISKRA Poznan University of Technology Poznan Poland

Prof. JAN KICINSKI Institute of Fluid-Flow Machinery -Polish Academy of Sciences Gdansk Poland

Prof. ZBIGNIEW KORCZEWSKI Gdansk University of Technology Gdansk Poland

Prof. JOZEF LISOWSKI Gdynia Maritime University Gdynia Poland Prof. JERZY EDWARD MATUSIAK Aalto University Espoo Finland

Prof. JERZY MERKISZ Poznan University of Technology Poznan Poland

Prof. VALERI NIEKRASOV Admiral Makarov National University of Shipbuilding Mikolaiv Ukraine

> Prof. JOZEF SZALA UTP University of Science and Technology Bydgoszcz Poland

Prof. TADEUSZ SZELANGIEWICZ Maritime University of Szczecin Szczecin Poland

> Prof. DRACOS VASSALOS University of Strathclyde Glasgow United Kingdom



POLISH MARITIME RESEARCH 2 (106) 2020 Vol. 27; pp. 120-124 10.2478/pomr-2020-0033

### ENERGY ANALYSIS OF THE PROPULSION SHAFT FATIGUE PROCESS IN A ROTATING MECHANICAL SYSTEM PART II IDENTIFICATION STUDIES – DEVELOPING THE FATIGUE DURABILITY MODEL OF A DRIVE SHAFT

Zbigniew Korczewski Konrad Marszałkowski Gdańsk University of Technology, Poland

#### ABSTRACT

The article presents a continuation of research carried out concerning identification of energy consequences of mechanical fatigue within a propeller shaft in a rotating mechanical system, while working under conditions of the loss of the required alignment of shaft lines. Experimental research was carried out on a physical model reflecting a full-sized real object: i.e., the propulsion system of the ship. It is proven, by means of an active experiment, that changes in propeller shaft deflection are reflected in the amount of dissipated kinetic energy of masses in rotational motion and the accumulated internal energy in its construction material. Adoption of a high-cycle fatigue syndrome, consisting of diagnostic symptoms determined from the action of the propeller shaft associated with the transformation of mechanical energy into work and heat, as well as with the generation of mechanical vibrations and elastic waves of acoustic emission, is proposed. To assess the diagnostic information quantity brought about by the defined features of propeller shaft fatigue, an experimental research program was developed and implemented, in which two statistical hypotheses are verified: the significance of the impact of the values enforcing the fatigue process, presented in the first part of the article, and the adequacy of the regression equation describing the fatigue durability of the propeller shaft in the energy aspect, constituting the second part of the article. This finally gives us the opportunity, after the appropriate translation of the model test results into full-sized real objects, to develop a methodology to diagnose marine propeller shaft fatigue in operating conditions. The third part of the article is devoted to this issue

Keywords: marine gas turbine, inlet air fogging, applicability

#### **INTRODUCTION**

Identification tests of the rotating mechanical system experimentally confirmed the lack of significance of the impact of one variable (of two) enforcing the drive shaft fatigue process associated with its rotational speed (statistically proven in the first part of this article); while searching for a mathematical function describing the process of shaft fatigue with respect to its durability, only one significant quantity forcing its deflection (fatigue) was taken into account: specifically, the load mass  $m_{load}$  [2,5,6].

Thus, an identification experiment based on the statically determined complete study plan of the physical system

was carried out. In this plan, the range of changes in the input value  $m_{loadc}$  was determined in the same way as for the elimination experiment – i.e., from 30 to 40 kg, at six levels of variability for the assumed values (every 2 kg), as shown in Table 1. The experiment also anticipated keeping the propeller shaft rotational speed constant at 1500 min<sup>-1</sup>. In each experiment, five repetitions of the recording of the observed control parameters of the rotary mechanical system were performed.

No.	Loading mass m <sub>load</sub> [kg]	Rotational speed of drive shaft <i>n</i> [min <sup>-1</sup> ]
1	30	1500
2	32	1500
3	34	1500
4	36	1500
5	38	1500
6	40	1500

#### **IDENTIFICATION STUDIES**

The main aim of the identification tests was to find a mathematical function describing the fatigue durability of the drive shaft  $\tau_w$  in terms of input (forcing) quantity values associated with an action of the rotary mechanical system in the form of work  $D_w$ , heat  $D_v$ , mechanical vibration generation  $D_{v}$ , and generation of acoustic emission elastic waves  $D_{EA}$  [1,4]. Assuming that the values of the individual forms of action are determined from measurements as extortions affecting the propeller shaft, the physical model of its fatigue process might be presented as the physical model shown in Fig. 1.



Fig 1. Physical model of propeller shaft fatigue process in a rotating mechanical system developed to determine its durability:  $D_w - propulsion$  shaft action associated with mechanical energy conversion in the form of working rotational motion;  $D_v - propulsion$  shaft action associated with mechanical energy conversion in the form of heat;  $D_v - propulsion$  shaft action associated with mechanical vibration generation;  $D_{EA} - propulsion$  shaft action associated with the generation of acoustic emission elastic waves;  $\tau_w - propeller$  shaft durability.

According to the adopted procedure, the determined plan of the experiment, and the set of input variables selected for the elaborated physical model, an analysis of their impact on the achieved fatigue durability of the propeller shaft was carried out. The results of testing the mechanical fatigue process of the shaft material, after conducting all the measurement sequences assumed in the experiment plan, are presented in Table 2. The result of each measurement series, each consisting of five repetitions, represents the arithmetic mean of the action value of the considered mechanical system expressed in J-s and its fatigue durability  $\tau_{wB}$ , expressed in s.

Table 2. Results of identification tests of the drive shaft mechanical fatigue process.

m <sub>load</sub> [kg]	D <sub>w</sub> [J·s]	$D_{_U}$ [J·s]	D <sub>v</sub> [J·s]	D <sub>EA</sub> [J·s]	$ au_{\scriptscriptstyle WB} \  ext{(tests)} \  ext{[s]}$
30	2.91·10 <sup>5</sup>	3.53·10 <sup>7</sup>	3.84.10-2	1.73.10-2	8718.2
32	1.79·10 <sup>5</sup>	2.18·10 <sup>7</sup>	2.31.10-2	1.04.10-2	5348.8
34	1.76·10 <sup>5</sup>	$1.77 \cdot 10^{7}$	1.12.10-2	9.91·10 <sup>-3</sup>	4258.2
36	$8.71 \cdot 10^4$	8.76·10 <sup>6</sup>	1.76.10-3	2.12.10-3	2086.2
38	8.23·10 <sup>4</sup>	$7.74 \cdot 10^{6}$	1.50.10-3	1.21.10-3	1828.6
40	6.19·10 <sup>4</sup>	5.94·10 <sup>6</sup>	7.77.10-4	1.48.10-3	1372.4

The final result of the experimental tests performed on the physical model of a real object (made on a scale) is a function describing the fatigue durability of the propeller shaft, which in a general form is expressed as follows:

$$\tau_W = f(D_W, D_U, D_V, D_{EA}) \tag{1}$$

In order to determine the fatigue durability function of the propeller shaft, the multiple regression analysis method was applied [9]. The purpose of a multiple regression is to quantify the relationships between many independent variables: i.e., the so-called explanatory ones. In the considered issue, there were variables characterising the action of the propeller shaft:  $D_{w}$ ,  $D_{v}$ ,  $D_{v}$  and  $D_{EA}$ . The dependent variable (the so-called explained one) is its fatigue durability  $\tau_{w}$ . In order to assess the impact of the input factors on the fatigue durability of the propeller shaft (with six levels of variation), the function of the test object takes a linear form, which for the considered case can be written as follows:

$$\alpha_{i} = \alpha_{0} + \alpha_{1} \cdot D_{Wi} + \alpha_{2} \cdot D_{Ui} + \alpha_{3} \cdot D_{Vi} + \alpha_{4} \cdot D_{EAi} + \varepsilon$$
(2)

 $\alpha_0 \div \alpha_4$  – estimated parameters of regression model;

i – level number of input factor variability;

 $\varepsilon$  – random component.

In the matrix form, this function is given by the following formula:

$$T_w = D \cdot \alpha + \varepsilon \tag{3}$$

where:

 $\tau_{Wi}$ 

$$T_{w} = \begin{vmatrix} \tau_{W1} \\ \tau_{W2} \\ \tau_{W3} \\ \tau_{W4} \\ \tau_{W5} \\ \tau_{W6} \end{vmatrix} \qquad D = \begin{vmatrix} 1 & D_{W1} & D_{W2} & \dots & D_{W6} \\ 1 & D_{U1} & D_{U2} & \dots & D_{U6} \\ 1 & D_{V1} & D_{V2} & \dots & D_{V6} \\ 1 & D_{EAI} & D_{EA2} & \dots & D_{EA6} \end{vmatrix}$$
$$\alpha = \begin{vmatrix} \alpha_{0} \\ \alpha_{1} \\ \alpha_{2} \\ \alpha_{3} \\ \alpha_{4} \end{vmatrix} \qquad \varepsilon = \begin{vmatrix} \varepsilon_{1} \\ \varepsilon_{2} \\ \varepsilon_{3} \\ \varepsilon_{4} \\ \varepsilon_{5} \\ \varepsilon_{6} \end{vmatrix}$$

In order to determine the parameters of the function describing the fatigue durability of the propeller shaft, the GRETL computer program, which is widely applied in econometrics [5], was used. The computational algorithms built into the program allow the user to quickly develop their own econometric models by means of using many methods of measurement data approximation. Due to the fact that the identification experiment program had only six levels of variability and the results obtained were characterised by a linear course, the least sum of squares method was applied to estimate the parameters of the linear model. As a result of the conducted analysis of many mathematical models using the GRETL program, only one was chosen because the best one describes statistically (with the highest coefficient of determination  $R^2$ ) the fatigue durability of a propeller shaft subjected to mechanical fatigue [10]. After taking into account the measurement data summarised in Table 2, the assumed function describing the fatigue durability of the propeller shaft is as follows:

$$\tau_W = -136.172 - 0.00155504 \cdot D_W + 0.000273696 \cdot D_U - -1116.11 \cdot D_V - 17602.4 \cdot D_{EA}$$
(4)

#### STATISTICAL ANALYSIS OF OBTAINED RESULTS

It was assumed a priori that the measurement results of all the control parameters ( $D_{w}$ ,  $D_{U}$ ,  $D_{v}$ , and  $D_{EA}$ ) characterising the propulsion shaft's fatigue are subject to random errors and the studied process is affected by various types of disturbances, also of an accidental nature [4]. Therefore, they were modelled as random variables of a normal distribution, with a specific, expected value and variation, as a measure of dispersion of the carried out measurements around the average value. It was also assumed that the variances of statistical data were equal or similar in value. Hence, a parametric statistical test for variance was used to assess the adequacy of the regression equation describing the considered fatigue process. Because these are tests with a one-sided critical area, verification of the hypotheses was based on Fisher–Snedecor *F* distribution statistics, comparing the calculated value of the  $F_{cal}$  test statistics with the critical (table) value  $F_{cr}$  of the distribution, calculated at the assumed significance level,  $\alpha = 0.05$ , and the number of degrees of freedom,  $f_1$  and  $f_2$  [7].

The following null hypothesis (denoted by H0) was verified in statistical identification tests of the propulsion shaft fatigue process:

# H0: The adopted mathematical model (regression equation) describing the fatigue durability of the propeller shaft is adequate.

If the calculated value of the  $F_{cal}$  test (empirical) statistics is greater than or equal to the critical value  $F_{cr}$  specified from the statistical table for a given level of significance and the number of degrees of freedom ( $F_{cal} > F_{cr}$ ), the null hypothesis should be rejected, considering that the adopted mathematical model is inadequate for the given significance level in the studied range of enforcing quantities.

The matching assessment of the model to the empirical data can be expressed by the determination coefficient which for this model is equal to  $R^2 = 0.999998$ . The Fisher–Snedecor *F* function for the adopted model is equal to  $F_{cal} = 140576.7$ . The critical value of the statistical coefficient for the degrees of freedom of the model – respectively,  $f_1 = 4$  and  $f_2 = 1$  – is equal to  $F_{cr} = 224.583$  [12]. Because  $F_{cal} > F_{cr}$  the statistics are located within the critical area of the distribution. Therefore, the zero hypothesis (H0) should be rejected in favour of the alternative hypothesis (H1). Thus, it can be concluded that at least one of the structural parameters of the shaft's fatigue durability model significantly differs from zero and, thus, at least one explanatory variable does not significantly affect the explained variable  $\tau_{wr}$ .

Adopting the model that is considered to be inadequate creates the possibility of making a second type of error. However, such an error was not made in assuming the model to be adequate, which is confirmed by the numerical values of the fatigue durability of the propeller shaft  $\tau_{WB}$  obtained from identification tests and the fatigue durability  $\tau_W$  determined using the mathematical model (4), as shown for comparison in Table 3.

In order to perform a comparative analysis of the determined values of the propulsion shaft's fatigue durability function and the results obtained from the experimental tests, the reference metric  $\delta T$  was applied [3]. Its dimensionless value constitutes a comparative indicator for all the developed mathematical models [10]. The smallest value of the reference metric indicates the mathematical model that best describes (in a quantitative sense) the fatigue durability of the propulsion shaft, as given in Table 3.

$$\delta T = \sqrt{\sum_{i=1}^{6} \left(\frac{\tau_{WB} - \tau_{W}}{\tau_{WB}}\right)^{2^{i}} \cdot 100\%$$
(4)

 Table 3. Results of identification tests of the propulsion shaft's mechanical fatigue process.

$D_w$ [J·s]	$D_{_U}$ [J·s]	$D_v$ [J·s]	$D_{_{EA}}$ $[J\cdot s]$	$ au_{WB}$ (tests) [s]	(model) [s]	Reference metric δT [%]	
2.91·10 <sup>5</sup>	3.53·10 <sup>7</sup>	3.84.10-2	1.73.10-2	8718.2	8715.0		
1.79·10 <sup>5</sup>	2.18·10 <sup>7</sup>	2.31.10-2	1.04.10-2	5348.8	5353.7		
1.76.105	$1.77 \cdot 10^{7}$	1.12.10-2	9.91·10 <sup>-3</sup>	4258.2	4259.1		
8.71·10 <sup>4</sup>	8.76.106	1.76.10-3	2.12.10-3	2086.2	2086.7	0.43	
8.23·10 <sup>4</sup>	7.74·10 <sup>6</sup>	1.50.10-3	1.21.10-3	1828.6	1830.9		
6.19·10 <sup>4</sup>	5.94·10 <sup>6</sup>	7.77.10-4	1.48.10-3	1372.4	1367.0		

#### FINAL REMARKS AND CONCLUSIONS

The statistical regression model proposed in this article is based on the linear nature of the fatigue process. The linear character of the propulsion shaft's fatigue durability model, subjected to a loss of required alignment (deflection), results from the application of an action function for its development. This function, in a physical sense, stands for the product of time and work of the fatigue destruction of the shaft's material. Due to the fact that the duration of the experiment is the same and common component for all (four) types of action (input factors), the obtained results of the experiments are characterised with a strong linear relationship and high correlation. For this reason, the application of the least sum of squares method to determine the regression coefficients of the regression equation is justified and allows for determination of the regression equation with a very large (close to unity) determination coefficient R2.

The low value of the reference metric confirms the adequacy of the developed propulsion shaft fatigue model, which may be a prerequisite for further research on its application in diagnosing fatigue of propeller shafts of real objects [11,13].

#### ACKNOWLEDGMENTS

The authors would like to thank the reviewers and Associate Editor for devoting patience, effort, and time to our manuscript. All the remarks and suggestions were justified, and we hope all have been taken into consideration in the revised version.

This project is supported by the statutory activity No 034158 of the Ministry of Science and Higher Education of Poland.

#### BIBLIOGRAPHY

 Kluczyk M., Grządziela A. (2017): Vibration Diagnostics of the Naval Propulsion Systems. Scientific Journal of Polish Naval Academy. 1 (208).

- 2. Korczewski Z. (2012): The Conception of Energetic Investigations of the Multisymptom Fatigue of the Simple Mechanical Systems Constructional Materials. Journal of Polish CIMAC, 7(1), 99-108.
- Korczewski Z. (2017): Diagnostyka eksploatacyjna okrętowych silników spalinowych – tłokowych i turbinowych. Wybrane zagadnienia. Gdańsk. Wydawnictwo Politechniki Gdańskiej.
- 4. Korczewski Z. (2017): A Method to Assess Transverse Vibration Energy of Ship Propeller Shaft for Diagnostic Purposes. Polish Maritime Research, 24 (4), 102-107.
- 5. Korczewski Z., Marszałkowski K. (2016): *Physical Model of Energy-Related Processes in a Rotating Mechanical System for the Purposes of Diagnosis of Transmission Shafts.* Journal of Polish CIMEEAC, 11(1).
- Korczewski Z., Marszałkowski K. (2018): Energy Analysis of Propulsion Shaft Fatigue Process in Rotating Mechanical System. Part I. Testing Significance of Influence of Shaft Material Fatigue Excitation Parameters. Polish Maritime Research, 25(1), 211-217.
- 7. Korzyński M. (2006): *Metodyka eksperymentu. Warszawa*. Wydawnictwa Naukowo-Techniczne.
- 8. Kufel. T. (2013): Ekonometria Rozwiązywanie problemów z wykorzystaniem programu GRETL. Warszawa. Wydawnictwo Naukowe PWN.
- 9. Maddala G.S. (2006): *Ekonometria. Warszawa*. Wydawnictwo Naukowe PWN.
- 10. Marszałkowski K. (2019): Modelowanie procesów energetycznych w obrotowym układzie mechanicznym dla potrzeb diagnozowania zmęczenia okrętowych wałów napędowych. Rozprawa doktorska. Politechnika Gdańska, Wydział Oceanotechniki i Okrętownictwa.
- 11. Murawski L. (2005): Shaft Line Alignment Analysis Taking Ship Construction Flexibility and Deformation into Consideration. Marine Structures, 18, 62-84.
- 12. Osińska M. (2007): Ekonometria współczesna. Toruń. Towarzystwo Naukowe Organizacji i Kierownictwa "Dom Organizatora".
- Vizentin G., Vukelić G., Srok M., (2017): Common Failures of Ship Propulsion Shafts. Scientific Journal of Maritime Research, 31, 85-90.

#### CONTACT WITH THE AUTHORS

**Zbigniew Korczewski** *e-mail: z.korczewski@gmail.com* 

Gdańsk University of Technology Narutowicza 11/12 80-233 Gdańsk **POLAND** 

#### Konrad Marszałkowski e-mail: konmarsz@pg.edu.pl

Gdańsk University of Technology Narutowicza 11/12 80-233 Gdańsk **POLAND**