

1 Waste management in the mining industry of metals ores, coal, oil and natural 2 gas - a review

3 **Szymon Kalisz**¹, **Katarzyna Kibort**¹, **Joanna Mioduska**¹; **Marek Lieder**¹; and **Aleksandra**
4 **Małachowska**^{1*}

5 ¹ Gdańsk University of Technology, Faculty of Chemistry, Department of Process
6 Engineering and Chemical Technology; szymon.kalisz@pg.edu.pl;
7 katkibor@student.pg.edu.pl; joanna.mioduska@pg.edu.pl; lieder@pg.edu.pl

8 * Correspondence: aleksandra.malachowska@pg.edu.pl; Tel.: +48584372637

9 **Abstract:** Waste generated due to mining activity poses a serious issue due to the large
10 amounts generated, even up to 65 billion tons per year, and is often associated with the risk
11 posed by its storage and environmental management. This work aims to review waste
12 management in the mining industry of metals ores, coal, oil and natural gas. It includes an
13 analysis and discussion on the possibilities for reuse of certain types of wastes generated from
14 mining activity, and discusses the benefits, disadvantages and the impact of waste
15 management on the environment. The article presents current methods of waste
16 management arising during the extraction and processing of raw materials and the threats
17 resulting from its application. Furthermore, the potential methods of mining waste
18 management are discussed through an in-depth characterization of the properties and
19 composition of various types of rocks. The presented work addresses not only the issues of
20 more sustainable management of waste from the mining industry, but also responds to the
21 current efforts to implement the assumptions of a circular economy, which is aimed at closing
22 the loop. The methods of recycling by-products and treating waste as a resource more and
23 more often not only meet environmental expectations, but also become a legal requirement.
24 In this respect, the presented work can serve as a valuable support in decision-making about
25 waste management.

26 **Keywords:** mining waste management, natural energy resources, metal-bearing ores,
27 chemical composition, environmental impact assessment

28 **1. Introduction**

29 Currently, in the world, open-pit and underground mines actively operate to extract valuable
30 metallic and energy resources (Radić et al., 2016). This paper focuses on six raw materials:
31 copper, lead, zinc (metallic raw materials) and coal, crude oil, and natural gas (energy raw
32 materials). The work focuses on analyzing the discussed raw materials relative to five
33 countries that are recognized as leaders in terms of resources and production of a given raw
34 material. For copper, these are Chile, Peru, China, USA, and the Democratic Republic of Congo
35 (DRC) (Flanagan, 2019; Kotarska et al., 2018); for zinc: China, Peru, Australia, USA, and India
36 (Maghfouri et al., 2018). Most lead is mined in China, Peru, the USA, Mexico, and Russia
37 (Mymrin et al., 2020). Oil and gas are mined in the USA, Russia, Saudi Arabia, Canada, the
38 United Arab Emirates, Iran, Canada, and China (Ismail et al., 2017). Among these countries,

39 only in the United States there are located all of the above-mentioned raw materials.
40 However, China is also at the forefront in terms of owned resources and their extraction,
41 except for crude oil.


42 Naturally, the large variety of raw materials found in the USA and China result from the
43 massive area of both countries, amounting to over 9 million km² (Brown et al., 2020). The wide
44 range of latitude and longitude determines a broad climatic spectrum for those countries,
45 which is conducive to the conditions for the formation of raw materials in the past and now.
46 Equally crucial for the formation of the discussed raw materials were tectonic movements and
47 the formation of the surface due to geological processes (Drachev et al., 2010; Mann et al.,
48 2005). It is worth emphasizing that the United States is situated on active tectonic plates, e.g.,
49 the San Andreas Fault, which runs through western and southern California, which is
50 characterized by rich sources of oil and natural gas (Mann et al., 2005).

51 Equally important for the formation of the discussed raw materials were tectonic movements
52 and the formation of the surface as a result of geological processes. It is worth to emphasize
53 that the United States is situated on active tectonic plates, e.g., the San Andreas Fault, which
54 runs through western and southern California, which is characterized by rich sources of oil and
55 natural gas (Mann et al., 2005).

56 In the case of China, the most active are 3 tectonic faults: Weibschuan, Pengguan, Baichuan,
57 causing cyclical shocks (4,000 movements in 15 years), contributing to mineralization and
58 filling in the resulting void spaces in rocks (Song et al., 2018).

59 Peru is rich in copper, zinc and lead, while Russia has the largest reserves of lead, oil and gas.
60 However, Russia is situated on one of the most stable tectonic plates - Eurasian, which reduces
61 the further mineralization of ores in this region of the world. Therefore, oil and gas originate
62 there from the existing geological formations . Other countries are the leaders for one or two
63 of the raw materials. Significant deposits of oil and gas are observed in the Arab states. In turn,
64 in Australia and India, the geology is characteristic of the presence of metalliferous elements
65 (Drachev et al., 2010; Flanagan, 2019).

66 Figure 1-6 presents countries with the largest deposits and the largest amounts of extracted
67 raw materials. The amount of produced waste was estimated based on the literature data.
68 The data in the graphs represent the resources that have been estimated and reported in
69 geological journals and texts (Bakalarz, 2019; Dudeney et al., 2013; Flanagan, 2019) for the
70 country concerned. The annual extraction of the raw material in a given country was
71 presented on the basis of data presented by the plants that extract the given raw material.
72 Data on the annual extraction of raw materials are also made public in official reports (Brown
73 et al., 2020). The amount of waste produced was estimated on the basis of data that includes
74 the amount of metal or raw material in the deposit and on the basis of reports that refer to
75 the ratio of the amount of raw material extracted to the amount of waste produced, expressed
76 as a percentage (Çoruh et al., 2012).



77


78

79

Figure 1. Countries with the largest resources of deposits, annual production and the average amount of waste produced from copper

80 The largest copper deposits are located in Chile (209 mln tones) and Peru (68 mln tones),
 81 wherein the annual extraction in Chile is more than twice that of Peru. The remaining
 82 countries, i.e., the Democratic Republic of the Congo, China, and USA have resources ranging
 83 from 20 to 35 million tons, with annual production 77% lower than that of Chile. Since the
 84 amount of raw material extracted is closely correlated with the amount of waste generated
 85 during the extraction process, the presented values indicate, why Chile produces 400% more
 86 waste than the Democratic Republic of Congo.


87 In Europe, Poland is the leader in extraction and production of copper. The biggest Polish
 88 producer, KGHM Polish Copper, extracts up to 702 thousand tons of raw material per year in
 89 total. With an average copper content of about 2% in Polish deposits, and extraction of 566
 90 thousand tons, over 28 thousand tons of copper ore flotation tailings are formed (KGHM,
 91 2020). During mineral enrichment, on average 94% of the material is treated as waste
 92 (Kotarska, 2012). Annually, Chile extracts about 60 times more copper than Poland and as
 93 much as 99% is waste. Both countries stockpile similar amount of flotation tailings,
 94 constituting 60-70% of the primary raw material (Łuszczkiewicz, 2000; Steliga and Uliasz,
 95 2012).



96

97 **Figure 2.** Countries with the largest resources of deposits, annual production and the
 98 average amount of waste produced from zinc

99 The highest zinc deposits are located in Australia (68 mln tones) and China (44 mln tones).
 100 Despite China deposits are around 35% less, it extracts about 3 times more than Australia.
 101 Similarly, to Peru, which has less than 3.6 times zinc deposits than Australia but extracts 7%
 102 more. The largest amount of waste from the zinc extraction processes is generated by China,
 103 reaching around 81.7 million tons, which is 307% more than in Peru, being second on the list
 104 (Amy C. Tolcin, 2020; Brown et al., 2020).




105

106 **Figure 3.** Countries with the largest resources of deposits, annual production and the
 107 average amount of waste produced from lead

108 The largest lead mineralization occurs in China, where the deposit's potential is 18 million tons
 109 and is approximately 2.8 times greater than the deposits in Russia or Peru and 3.2 times
 110 greater than in the other countries. China is the undisputed leader, when it comes to mining




111 of lead, since it brings it out 700% more than other countries. Similarly, as in the case of the
 112 aforementioned metalliferous raw materials, China is also an inglorious leader in terms of
 113 waste generated from the lead mining process (Yin et al., 2020).




114
 115 **Figure 4.** Countries with the largest resources of deposits, annual production and the
 116 average amount of waste produced from coal

117 Coal deposits found in the United States are estimated at around 250,000 million tons, while
 118 smaller resources, ranging from 105,000 million tons to about 150,000 million tons, are in
 119 India, China and Australia (“Coal and lignite production,” 2019). Annually, Chinese coal
 120 production is about 4,000 million tons, while other forefront countries extract 85% less. This
 121 is related not only to smaller coal deposits, but also to climate policy. However, coal waste
 122 accounts for approximately 46% of the annual output for each of the leaders (Fečko et al.,
 123 2013).



124
 125 **Figure 5.** Countries with the largest resources of deposits, annual production and the
 126 average amount of waste produced from oil

127 The majority of crude oil extraction is carried out by Arab countries, such as the United Arab
 128 Emirates, which has 97,800 tcm (trillion cubic meter) and Saudi Arabia having less than half of
 129 the deposits of the United Arab Emirates. However, despite having the biggest resources,
 130 these countries are not producing the most. The leader is the United States, which despite
 131 having 92% smaller oil deposits than the United Arab Emirates, extracts it up to 415% more
 132 (“Crude oil production,” 2019).



133

134 **Figure 6.** Countries with the largest resources of deposits, annual production and the
 135 average amount of waste produced from gas

136 Russia has the largest natural gas reserves in the world, estimated at 38 tcm, which is 16%
 137 more than the estimated natural gas deposits in Iran. Similarly, to the crude oil, despite not
 138 having the biggest resources, the USA is the largest producer of this raw material. Iran, Canada
 139 and China produce similar amounts, despite large differences in their resources. Compared to
 140 the US, annually they extract around 77% less (“Natural gas production,” 2019). Charts with
 141 regard to global extraction, resources and waste from metals, and energy raw materials are
 142 presented in the appendix (Fig I and Fig II).

143 Data on resources and annual production (Fig. 1 - Fig. 6) show what sizes of raw materials
 144 individual countries have. The distribution of the share of the distinguished countries has been
 145 similar so far, as it corresponded to the resources held. However, the situation has recently
 146 changed due to the prevailing pandemic. As a result of sanitary restrictions and people
 147 infected with covid-19, the efficiency of mines decreased due to the limited number of
 148 working personnel. In some countries, mining activities have been reduced or terminated,
 149 such as South Africa, where the shutdown of the mining process led to the closure of mines
 150 and the dismissal of workers. The restrictions led to the suspension of many industrial and
 151 construction productions, which led to a dramatic drop in demand for metals. There has been
 152 a decline in the prices of metals and minerals, mainly aluminum (down 15%), copper (down
 153 14%), gold, lead and nickel, thereby putting the incomes of countries based on exploration of
 154 raw materials at risk (Laing, 2020).

155 The introduced restrictions related to movement affected the transport sector, including
156 aviation, and this in turn affected the fuel market. These sectors accounted for 60% of the oil
157 demand. As a result of the pandemic, demand decreased from 100 million barrels in January
158 2020 to less than 75 million barrels in April 2020. The International Energy Agency (IEA)
159 predicted that global demand for natural gas in 2020 will decrease by 4 %. From December
160 2019 to June 2020, the number of drilling and gas rigs in the US decreased from 805 to 265.

161 Downtime caused by the pandemic contributed to the lack or problems with the availability
162 of certain materials on the market, and this also contributed to a sharp increase in the prices
163 of metal raw materials as well as oil and gas (Moore et al., 2020; Nyga-Łukaszewska and Aruga,
164 2020; Zanoletti et al., 2021).

165 This work aims to review waste management in the mining industry of metals ores, coal, oil
166 and natural gas. It includes an analysis and discussion on the possibilities for reuse of certain
167 types of wastes generated from mining activity, and discusses the benefits, disadvantages and
168 the impact of waste management on the environment.

169 To meet the goal and to discuss waste management according to its characteristics, the
170 research begins with the review on the properties and composition of metal-bearing ores and
171 energy rock resources. Furthermore, it compares it with the variability in mineralogical
172 composition of the wastes generated during processing and production. This knowledge and
173 understanding of the technology of wastes acquisition allows estimating the amount
174 generated, the variability between particular processes, and evaluate best and most
175 environmentally friendly way of its future re-use and management.

176 The literature reviewed and placed in this paper, was selected in such a way as to present the
177 world resources, annual extraction of selected metals and energy raw materials, and
178 estimated amounts of produced waste, in order to show the scale of the amount of waste
179 produced and the related management possibilities. The authors focused not only on
180 published data in articles, but also on information that is available in individual mines and
181 companies. Furthermore, a literature review was carried out on the geological basis of metals
182 and energy raw materials, and mineralogical and phase composition of mine waste. These
183 compositions vary according to the publication dates of the manuscripts. These differences
184 result from technological changes in individual mining and material processing plants.
185 Therefore, the authors chose the latest publications. On this basis, current data on the
186 management of the above-mentioned waste and new possibilities of their use were
187 presented.

188 **2. Geological aspects**


189 A comprehensive analysis of the raw materials discussed in this paper is important as the aim
190 is to analyze both the waste and the structure of the base component, which contain valuable
191 minerals that end up in the waste. Due to their value, the raw material and accompanying

192 rocks should be managed as best as possible, for example to produce a new product
 193 (concretes, coatings, pavements), but also to reduce possible environmental toxicity.


194 *2.1. Copper, zinc and lead*

195 Copper is a metalliferous raw material obtained from rocks. It is extracted over 87-90% from
 196 sulphide ores and up to 9-12% from metal oxides (“Przeróbka kopalni miedziowych,” 2008).
 197 Zinc and lead are also obtained from rock ores.

198 Acquiring raw materials for copper, zinc and lead requires mining them along with the rock in
 199 which they are contained. The raw material is extracted from the rock by means of flotation,
 200 whereas the remnants are considered as useless waste. Native copper ore deposits are
 201 extremely rare and constitute only about 1% of all its mineral deposits (“Copper alliance,”
 202 2018, “Informator Metale Nieżelazne,” 2005). The mineralogical compound of rock waste
 203 results from the types of geological layers that may vary from region to region. The compound
 204 of copper ores for selected types of rocks are presented below. The main constituent is a
 205 gangue, which accounts for over 90% by weight, while copper minerals are less than 1 wt%.
 206 In the Figure 7 and Figure 8, copper is indicated in the "other" group along with other
 207 compounds of metallic origin in small amounts (Matlakowska et al., 2014).



208
 209 **Figure 7.** Mineralogical compound of shale rocks (left) and marls (right) containing Cu
 210 minerals




211
 212 **Figure 8.** Mineralogical compound of Zechstein limestone (left) and spotted marls containing
 213 Cu minerals

214 Copper mineralization is observed in various types of rocks. Copper compounds are contained
 215 in igneous and sedimentary rocks of the Sierra Gorda deposit - the largest copper-
 216 molybdenum ore deposit in the world, located in the Atacama Desert in Chile. Copper occurs
 217 there in the form of sulphides and oxides in granodiorite, granite and monzodiorite rocks. Due
 218 to the large area of the deposit, the mineralization of the raw material also took place there
 219 in volcanic rocks, mainly in tuffs and andesites, and mudstones and claystones of sedimentary
 220 rocks (López and Ristorcelli, 2011; Pieczonka et al., 2017; Ristorcelli, S., Ronning, P., Fahey, P.
 221 and Lustig, 2008). Copper compounds in sedimentary rocks are also found in Polish copper
 222 deposits, which have been mineralized in shales, dolomites and sandstones. (Kibort and
 223 Małachowska, 2018; Konopacka and Zagożdżon, 2014).

224 Copper is also contained in Chinese sandstone deposits in the Chuxiong Basin. Sandstones are
 225 the result of the formation of geological features in the Cretaceous. Copper mineralization is
 226 visible in rock deformations (faults, anticlines, crevices) and in places that contacted with
 227 water. A shale zone is also distinguished there, which is consistent with the Permian copper
 228 shale from the European region. Copper minerals are mainly observed in the form of lenses
 229 and dominant thin lamination (Chen et al., 2000; Hsi-chi et al., 1968; Huang et al., 2019)

230 The quantity of the extracted raw materials is influenced by the rock texture of the sediment
 231 deposits, in which the raw material occurs. Thus, it is important to consider the texture when
 232 analysing the potential of any resources for production (Kibort and Małachowska, 2018).
 233 Copper in rocks can occur in different forms, what is graphically presented in Figure 9: – it
 234 occurs as dispersed or finely dispersed, filling rock spaces, e.g., in sandstones, – mineralized
 235 veins, usually occurring according to the location of the rock layers (shales), and – irregular
 236 sockets, known as lenticular, characterized by an oval shape observed in the form of lenses
 237 and dominant thin lamination (Chen et al., 2000; Hsi-chi et al., 1968; Huang et al., 2019, Kibort
 238 and Małachowska, 2018; Oszczepalski et al., 2019).




239 **Figure 9.** Forms of copper: A - dispersed, B – mineralized veins, C – lenses

240 Zinc and lead are most often found in the form of a single ore and are mostly extracted from
 241 sulphide ores. In the recent years zinc has been obtained by the hydrometallurgical method
 242 using electrolysis (Cabała, 2010). In its native state, zinc does not occur naturally. The main
 243 minerals of zinc are zinc blende (sphalerite - zinc sulphide) and smithsonite (zinc carbonate).
 244 Zinc blende is the most important zinc ore, containing also large amounts of cadmium, lead
 245 and even silver, indium and gallium (Kołodziejczyk, 2019). Cadmium accompanies almost all
 246 zinc ores.

247 The most important lead ores are galena (PbS - lead (II) sulphide) and anglesite (PbSO₄ - lead(II)
 248 sulphate). Galena is found in igneous and sedimentary rocks. It is accompanied by compounds
 249 of antimony, bismuth, zinc, copper, silver, gold and iron. Most often it contains only a few
 250 percent of lead, while pure lead sulphide may contain it up to 86%. In the case of zinc and
 251 lead, similar forms of occurrence are observed as in the case of copper, and the mineralization
 252 and distribution depend on the hydrogeological and thermal conditions. The presence of zinc
 253 and lead minerals in carbonate rocks is associated with hydrothermal processes of transfer of
 254 compounds from lower geological formations to the higher layers containing sulfur
 255 compounds, forming compounds with zinc and lead. Another source is the deposition of lead
 256 zinc in carbonate layers as a result of entering the cooler layers, preventing dissolution of the
 257 elements and further penetration (Van der Graaf, 2018). In Figure 10 are mineralogical
 258 compound of dolomite containing zinc minerals and marls containing lead minerals with the

259 minerals Zn and Pb being classified in the group "other". Zn and Pb content did not exceed 1
 260 wt.% (Biernacka et al., 2005).



261
 262 **Figure 10.** Mineralogical compounds of dolomite (left) containing Zn minerals and marls
 263 (right) containing Pb minerals

264 The largest zinc mineralization was observed in dolomite sedimentary rocks and smaller in
 265 igneous rocks (Abu-Hamattah and Al-Amr, 2008; Höller and Gandhi, 1997). To a lesser extent,
 266 the mineralization of zinc and lead is observed in metamorphic gneiss in the form of sulphide
 267 ores of the Ramura-Agucha deposit and graphite-mica-sillimanite shales (Kumar, 2013). A
 268 similar situation of mineralization is observed in the Barney Creek Formation in Australia,
 269 where zinc and lead deposits are mostly found in dolomite and shale rocks (Haines, P.W.,
 270 Pietsch, B.A., Rawlings, D.J., Madigan, T.L., Findhammer, 1993; Hughes, 1990; Page et al.,
 271 2000). The mineralization of zinc and lead compounds is observed in an overhang of gneiss
 272 strands of the Rampura-Agucha deposit in the form of sphalerite and galena. They are in the
 273 form of fine to coarse grains with inclusions of feldspar, quartz, sillimanite and chlorite
 274 (Kumar, 2013).

275 A similar condition occurs in the European region with zinc and lead, referred as MVT deposits
 276 (Mississippi Valley Type). The name results from the similarity of the properties of the deposit
 277 to the compounds found in the Mississippi River Valley. The largest European zinc-lead region
 278 is located in Poland and is characterized by the presence of raw materials in carbonate rocks,
 279 the mineralization of which dates back to the period from the Devonian to the Jurassic.
 280 According research (Gałkiewicz and Śliwiński, 1983), the mineralization of zinc and lead
 281 follows tectonic structures (PIG-PIB, 2020; Piwowarski and Żeglicki, 1977).

282 Zinc deposits associated with carbonate rocks are also observed in Iran, where they are found
 283 in the Dolomites and Lower Permian dolomitic limestones. A characteristic feature of this
 284 deposit is the absence of zinc sulphides. Below the layer of zinc-lead ore deposit, there are
 285 shales and sandstones, and above gypsum, sandstone and shale rocks (Maghfouri-Moghadam
 286 et al., 2009).

287 The forms of zinc and lead minerals are described as similar to those of copper. They fill gaps
288 and tectonic breaches. The most common are lenticular forms, as well as nests, stockworks
289 and lines, which occur according to the stratification of the ore deposit (Nieć et al., 2018;
290 Piwowarski and Żeglicki, 1977)

291 2.2. *Coal*

292 Coal mining is associated with the acquisition of the raw material along with accompanying
293 rocks. Occurring coal seams are characterized by a different geology and period of formation.
294 Such condition can be observed in the Chinese layered coal seam structure, where the
295 influence of the marine environment on the geology of accompanying rocks is undoubtedly
296 visible. Those coal seams are mainly associated with sedimentary rocks including sandstones
297 and to a lesser extent mudstones and bauxite. Lime inclusions also appear there (Fang et al.,
298 2013; Jin et al., 2013). Carbon stratification by sedimentary rocks is also observed in the
299 European region. An example is the Upper Silesian Coal Basin, in which sandstone may
300 constitute from several to 70% of the accompanying rocks. Further west, the sandstone
301 content is lower, while claystone and shale predominate (Galos and Szlugaj, 2010)

302 2.3. *Crude oil and natural gas*

303 The drilling sector is characterized by a wide spectrum of rocks extracted as a drilling waste,
304 which is influenced by the location and depth of the drilling that may pass through several
305 significant and minor geological strata. For example, the geology of oil and gas fields in the
306 Gulf of Mexico is made up by an alternation of shales and sandstones at a depth of 5,000-
307 5,300 m. Carbonate rocks also appear in the lower section of the well (approx. 6,000 m)
308 (British Petroleum, 2010; Dice, 2017). Further down, from about 6,800 m to 7,500 m, salt
309 deposits are present (“bp Statistical Review of World Energy,” 2020, “Natural gas production,”
310 2019; Dice, 2017)

311 Sandstones and sandy clays constitute the rock layers of the Baltic hydrocarbon deposits.
312 Quaternary clays also occur with them. Free rock spaces are most often filled with silt or
313 organic material. The Northern Baltic Sea Basin is characterized by the transition of sandy
314 rocks into clay, loams and mudstones. Therefore, it can be concluded that the Baltic region
315 consists of those four rock types (Sikora and Wojna-Dyłaż Elżbieta, 2010).


316 **3. Properties of mining and processing waste**

317 Mining and processing of rocks and metal ores generates large amounts of waste rocks,
318 (gangue), from the extraction process, tailings (from flotation and enrichment) and
319 metallurgical waste (from the smelter).

320 During metal processing in a smelter, a waste called slag is produced (Gorai et al., 2003). The
321 extraction of copper in one mine generates an average of 2.3 million tons of waste per year
322 (Çoruh et al., 2012). Similarly, in the case of zinc and lead, 1 ton of extracted metal generates

323 19 tons of flotation waste and gangue (Bouguermouh et al., 2018). Figure 11 presents a
324 general scheme of how metal raw materials are processed.


325



326 **Figure 11.** Diagram of the extraction of metal raw materials

327 Processing of energy resources such as coal, oil or gas, as in the case of metals, produces liquid
328 waste, and solid waste - drill cuttings. As a result of coal mining, a waste rock, in the case of
329 coal constitute about 30% (Kopacz, 2015), and the rest of the generated waste are tailings
330 containing gangue and large amounts of water, which is recycled in a closed circuit (Hudson-
331 Edwards et al., 2011).

332 The oil and gas industry also produces specific waste, known as drilling (around one million
333 tons) and cuttings. The extraction of raw materials generates waste rock, such gangue and
334 drill cuttings (Huang et al., 2018) as well as drilling and fracturing fluid. A general diagram of
335 waste generation during the extraction of crude oil and natural gas is shown in Figure 12



336 **Figure 12.** Diagram of waste generation during the extraction of crude oil and natural gas

337 **3.1. Copper, zinc and lead**

338 The extraction of copper, zinc and lead ores as well as the processing of these raw materials
 339 affects the quality of the environment. Mines produce a large amount of waste because the
 340 metal-containing ore is a small fraction of the total volume of material extracted. The waste
 341 material is generated in the processes of mining, extraction, processing and further treatment,
 342 and its quantity depends on a number of factors related to the geological structure of the rock
 343 mass, the quality of the deposits, methods of excavation and enrichment technology (Baic and
 344 Witkowska-Kita, 2011; Galos and Szlugaj, 2014; Tumidajski et al., 2008).

345 Mining waste constitutes mainly gangue, which is removed at the stage of deposit
 346 preparation, and waste from the extraction and processing of the raw material. The amount
 347 of the waste depends on the type of a mine: whether it is underground or open-pit. The waste
 348 from mining and preparatory works includes those generated, among others, while drilling
 349 new shafts. They are characterized by high variability of petrographic composition. The share
 350 of clay, sandstone, mudstone and overgrowth is varied. The grain composition of this material
 351 is in the range of >300 mm. In open-pit mines, the surface material is called an overburden,
 352 which is used to backfill the place, where the raw material was mined.

353 The waste from processing operations includes coarse-grained scrubber waste, grain class 20–
 354 200 mm; medium-grain waste from jigs, grain class 2–20 mm and fine-grain waste from spirals,
 355 grain class 0.5–2.0 mm. The content of organic parts in the waste material ranges from 42%
 356 in the case of jigs to 60% in the case of spirals. The mineral content ranges from 58 to 40%,

357 respectively. The processing waste also includes sludge waste. They come from a chamber and
358 belt presses. These are very fine-grained waste with a grain size of less than 0.5 mm. In terms
359 of petrography, they are characterized by a significant share of clay and coal.


360 3.2. Coal

361 Coal mining, in relation to the production of other raw materials discussed in this study,
362 generates the least amount of solid waste, which is managed through landfilling. The
363 generated waste mainly comes from accompanying rocks that are separated in the froth
364 flotation process. The waste from flotation can be further subjected to an enrichment (Melo
365 and Laskowski, 2006). Wei et al. 2015, (Wei and Peng, 2015) used a diesel collector for coal
366 flotation, while methyl isobutyl carbinol (MIBC) was used as a frother, while Peng2015 used
367 N-dodecane and 2-octanol as a collector and frother. From the literature review it is seen that
368 oily reagents are commonly used, despite they should be neutralized before storage.

369 3.3 Oil and gas

370 The extraction of crude oil and natural gas involves drilling. Wastes from oil and gas extraction
371 are mainly drill cuttings from drilling holes, contaminated drilling mud to facilitate production
372 operations. The chart below shows an example of the cuttings mineralogical composition,
373 which is the average value for ten depths within the range from 2500 to 5000 m. The main
374 minerals of cuttings are quartz, feldspar, calcite and clay minerals. The content of each of them
375 ranges from about 21 to 26%. Dolomite has the lowest content equal to 4.1%.

376



377


378 **Figure 13.** Example of mineralogy of drill-cuttings

379 Drill cuttings variability in composition may be the result of natural geological processes or the
380 result of contamination with components of water or oil-based drilling fluids. The group of
381 liquid contaminants also includes the fracturing fluid consisting of 90 to 95% of water and
382 chemical additives. To reduce the resource consumption, the flowback fluid from the
383 fracturing process is treated and reused (Steliga and Uliasz, 2012).




384 Drilling works are carried out to the point of contact with the source hence the drill cuttings
385 and drilling fluid are slightly contaminated with crude oil. This qualifies them as harmful to
386 the environment and intended for disposal or neutralization. The chemical composition of
387 drilling fluids can also contaminate solid and water wastes. There are three most popular types
388 of drilling fluids: water-based, oil-based and pneumatic (Eldridge, 1996; Pereira et al., 2019),
389 the compositions of which are shown in Figure 13.

390 Water-based drilling fluids, such as synthetic ones, have a minimal impact on the environment
391 and can therefore be disposed offshore. As most harmful and toxic drilling fluids are
392 considered those based on oils. That type cannot be returned to the environment without
393 purification and neutralization processes (Kujawska and Pawłowska, 2020). Types of drilling
394 fluid is presented in Figure 14 according to (Ismail et al., 2017). Similarly, as petroleum-based
395 fluids, which are not permitted for offshore disposal and generated drill cuttings need to be
396 cleaned prior to storage.



397 **Figure 14.** Types of drilling fluid

398 In turn, synthetic-based drilling fluids are preferred due to their technical characteristics and
399 minimal environmental impact. An exemplary composition of the drilling fluid is shown in
400 Figure 15 (Ismail et al., 2015).



401 **Figure 15.** An example of a drilling fluid


402 **4. Composition of waste from mining activity**

403 The composition of waste from raw material extraction was analyzed in terms of the following
 404 compounds: SiO₂, Fe₂O₃, Al₂O₃, TiO₂, CaO, CuO, ZnO, PbO, PbO₂, Cr₂O₃, SO₃, K₂O and MgO.

405 The main components of flotation process of copper are silica (SiO₂), which comprises from
 406 27% to 59%, and iron oxide (III), Fe₂O₃, representing from trace amounts up to 65% (Çoruh et
 407 al., 2012). The basic components of zinc and lead flotation waste are calcium oxide, CaO (up
 408 to approximately 26%), iron (III) oxide (approximately 12%), magnesium and sulfur oxides
 409 (around 11% each) and silicon dioxide (8.4%). Copper minerals constitute up to 1 wt.%. while
 410 lead minerals up to approx. 0.3 wt.%. In Figure 12, both Cu and Pb are grouped as 'other'.
 411 Other compounds such as Al₂O₃, Na₂O, K₂O, TiO₂, P₂O₃, As₂O₂, PbO₂, ZnO, Cl are present in
 412 trace amounts (Bakalarz, 2019; Çoruh and Ergun, 2006; Grudinsky et al., 2020; Kowalczyk,
 413 2019; Koziół and Uberman, 1996; Liu et al., 2020; Nowak, 2008; Stanojlović and Sokolović,
 414 2014; Steliga and Uliasz, 2012). Figure 16 shows averaged data of the content of mineralogical
 415 compounds in the post-flotation tailings based on the analysis of literature data from (Lutyński
 416 and Szyrka, 2010; Rad and Modarres, 2017) the recognized compounds comply with the
 417 deposit geology (Alp et al., 2008; Çoruh et al., 2012;). The identified compounds are consistent
 418 with the previously described geology of copper, zinc and lead deposits. Depending on the
 419 occurrence of the rock formation, they may differ in the intensity (% content) of the
 420 occurrence of individual mineralogical compounds.


421 Post-flotation waste from the processes of obtaining zinc and lead was analyzed on the basis
 422 of two authors what is presented in Figure 12 (Nowak, 2008; Śliwka et al., 2019). The average
 423 values indicate more even distribution of components than in the case of copper waste. Zinc
 424 and lead wastes are characterized by the highest CaO content, ranging from 26% to 29%,
 425 which is consistent with the typical geology of the deposit. A lower content was recorded for

426 MgO (15%), Fe₂O₃ and SiO₂ (about 12% each) and SO₃ with a content up to 9%. There was no
 427 presence of CuO, PbO and Cr₂O₃. (Asadi et al., 2017; Muravyov and Fomchenko, 2018). Other
 428 compounds such as Al₂O₃, K₂O, TiO₂, P₂O₃, PbO₂ are present in trace amounts. Zn minerals
 429 constitute up to 3 wt.%, while minerals Pb approx. no more than 0.3 wt.%. Both Zn and Pb are
 430 presented in the Figure 12 as components of the "other" group.




431
 432 **Figure 16.** Mineralogical compounds of post-flotation waste from Cu ores (left) and Zn and
 433 Pb ores (right)

434 Figure 17 shows the results of the average mineralogical compound of coal flotation waste are
 435 the average value based on the results presented by research groups (Kara, 2014; Lutyński
 436 and Szpyrka, 2010; Piszcz-Karaś et al., 2019; Rad and Modarres, 2017). The highest content
 437 was recorded for silica (39% - 60%) and Al₂O₃ (c.a. 17.5%). The content of the remaining
 438 components was ranging from 1.5% to about 5%. The compounds like CuO, ZnO, PbO, PbO₂,
 439 Cr₂O₃ were not recorded in the composition of coal waste.



440
 441 **Figure 17.** Mineralogical compounds of coal post-flotation waste (left) and coal ash (right)

442 The mineralogical compound of waste and drill cuttings obtained as a result of oil and gas
 443 extraction works varies depending on the existing geological layers, what is shown in Figure
 444 18 (Chen et al., 2000; Çoruh et al., 2012; Hsi-chi et al., 1968; Huang et al., 2019; Kibort and
 445 Małachowska, 2018; Konopacka and Zagożdżon, 2014; Longarini et al., 2014; López and
 446 Ristorcelli, 2011; Nowak, 2008; Pieczonka et al., 2017; Ristorcelli, S., Ronning, P., Fahey, P. and
 447 Lustig, 2008). Wastes from oil and gas extraction are mainly rocks contaminated with
 448 components of drilling fluid. Drilling waste compounds were analyzed on the basis of 4
 449 literature sources by (João et al., 2017; Köse, 2019; Piszcz-Karaś et al., 2019; Rykusova et al.,
 450 2020). The average result of drilling wastes shows that the silica content was over 60%, Al₂O₃
 451 was 13% and CaO was 8%. The content of Fe₂O₃, K₂O, MgO and SO₃ ranged from 1.5 to 4%.
 452 The remaining components were characterized by the content below 1%, except for PbO and
 453 PbO₂, which were not present.



454
 455 **Figure 18.** Mineralogical compounds of cuttings from oils & gas sector

456 **5. Waste management**

457 **5.1. The current state of post-mining waste management**

458 The most popular method of post-flotation waste management is ground storage in waste
 459 neutralization tanks. In Europe, the largest landfill and a facility for neutralizing copper
 460 flotation waste is the “Żelazny Most Mining Waste Treatment Plant”, owned by KGHM Polska
 461 Miedź, located in the Lower Silesia in Poland. The facility, where the waste is stored, is limited
 462 by the embankment, which is designed to prevent the waste from scattering. There is a
 463 pipeline in the upper part of the shaft to transport sewage by water. When waste is deposited,
 464 it spontaneously segregates: coarse-grained material falls close to the discharge point to form
 465 a beach, and water and dust flow to the landfill to form a sedimentation basin. Recycled water
 466 from the drained sediment is used in the flotation process (Çoruh and Ergun, 2006; Grudinsky
 467 et al., 2020; Kowalczyk, 2019) In the Żelazny Most also liquid flotation waste (sewage) from
 468 copper extraction is stored. Table 1 presents the parameters of the Żelazny Most waste
 469 treatment facility, the current state and assumptions for the coming years (Grabas and Pawlik,
 470 2017).

Table 1. Parameters of the 'Żelazny Most' Mining Waste Treatment Plant

Parameters	Size	
	Present	Future
Total area [km ²]	16	22
Total collected waste [mln m ³]	560	969
Length of embankments [km]	14.3	-
Maximum dam height[m]	36-62	over 100
Poolarea [km ²]	7.5-8	-
Beach area [ha]	794	-

472 In appendix are photos of the largest places disposal of post-flotation waste (Figure IV). The
 473 areas of the reservoirs range from about 8 up to 20 km². For economic and logistical reasons,
 474 they are located in the vicinity of the mine.

475 A good pro-environmental solution is afforestation of brownfield sites. The literature is rich in
 476 research on the use of plant cover as a method of reviving such sites. The use of specific types
 477 of trees can have very good effects on people and the environment (Ciarkowska et al., 2017;
 478 Ciarkowska and Hanus-Fajerska, 2008; Mleczek et al., 2016).

479 Selected species of trees and plants can contribute to the increase in the content of organic
 480 matter in the soil and the development of a soil system capable of meeting the nutrient and
 481 water needs of other plants and microorganisms. Hence, the introduction of specific trees
 482 might be also an effective tool in reducing the risk of damaging dams prior to surface water
 483 migration.

484 Waste from coal mining is managed, however only in 44%. Among the waste related to coal
 485 mining and processing, the following types of waste are distinguished: flotation, slag, bottom
 486 ash and fly ash. Post-flotation waste may be subjected to the enrichment process; slag - can
 487 be used in construction as a material used in civil engineering (road construction), it can also
 488 act as a sealing material. Bottom ash is a good filter material or, after appropriate
 489 transformation, can be used as fertilizer or granulate for plants, while fly ash is mainly used in
 490 construction. Researchers (Lazutkina and Buler, 2003) proposed the use of carbon ash (an
 491 aluminosilicate material) mixed with borax to create glass coatings on steel surfaces in order
 492 to protect the steel from deformation at high temperatures.

493 Fly ash is deposited in ash dumps in Australia and half of this is processed into beneficial
 494 products such as concrete ("Unearthing Australia's toxic coal ash legacy," 2019). The global
 495 average of coal ash reuse is 53%, wherein India reuses 61%, the UK 70% and Japan 97%. In
 496 turn, in China waste constitutes 10-15%, and only 69% is managed, which gives about 535
 497 million tonnes of unused waste (Maiti and Pandey, 2020; Pacholewska et al., 2007). Waste
 498 from coal processing and coking plants may contain valuable components. Pavlovich et al.
 499 (Pavlovich et al., 2004) proposed the use of phthalic anhydride, present in post-processing
 500 waste, as a raw material for the production of anti-corrosion and abrasion-resistant products.

501 One common method of mining waste management is underground storage, used among
502 others for backfilling workings and sealing goafs, when there is too much waste from current
503 production, which cannot be used otherwise. Waste management through underground
504 storage is used mainly in the extraction of natural aggregates, where can be used to neutralize
505 mine drainage and post-flotation sewage (Meggyes et al., 2008).

506 In order to manage drilling cuttings and mining waste, similarly as in the case of post-flotation
507 waste, a landfilling is used. However, this method requires the pretreatment of drill cuttings,
508 since they can contain heavy metals in an amount exceeding the permissible levels regulated
509 by applicable law (*Announcement of the Marshal of the Sejm of the Republic of Poland of*
510 *October 8, 2020 on the publication of the uniform text of the Act on mining waste, Dz. U. 2020,*
511 *pos. 2018, 2020; Europejski and Unii, 2006). Otherwise, storage of untreated drill cuttings in*
512 *designated areas or agricultural areas may result in the release of undesirable components*
513 *into the soil and groundwater, causing contamination. On average, one well can produce*
514 *about 1,000 m³ of solid waste – drill cuttings, and from 800-1,200 m³ of liquid waste (Kujawska*
515 *et al., 2016; Steliga and Uliasz, 2012). In selected European countries, such as in Poland,*
516 *gangu - drill cuttings, is managed in 86%, however mainly by landfilling.*

517 Based on the types of contamination, there are 3 options for the disposal of drilling waste:

- 518 • disposal at sea,
- 519 • land disposal,
- 520 • re-injection into the drilling field, reconstruction of the well.

521 Waste treatment methods differ among countries. Almost always, disposal at sea or on land
522 is restricted by regulations and most often is associated with additional restrictions as to the
523 storage of hazardous substances on unsecured areas. Drilling cuttings, in the form of solid
524 waste, require treatment of oily substances and storage in adapted landfills. Solid and toxic
525 waste need storage in special, sealed tanks. Re-injection of drill cuttings into the well is a
526 favorable disposal option, if the drilling waste is not contaminated and has been subjected to
527 pretreatment process (Permata and McBride, 2010).

528 5.2. Closed water circuit

529 Proper management of water used in the flotation process and the extraction of raw materials
530 is a very important element from economic and environmental point of view. Due to the
531 potential risk of soil contamination, and thus the negative impact on plants and animals,
532 researcher carry out studies on the biological purification and treatment of water and its reuse
533 in technological processes related to mining (Daldoul et al., 2019; Shengo and Mutiti, 2016).
534 The flotation process can be used for water treatment, as shown in the article (Rubio et al.,
535 2002).

536 The quality of the water used in the flotation, as well as pH and the content of dissolved solids,
537 are of great importance for the process efficiency. To obtain optimal conditions, it is
538 recommended to use both recycled water and water from the network (Farrokhpay and Zanin,

539 2012; Lin et al., 2020). However, water recycling in a closed loop is also desirable and
540 considered as capable of reduction the number of reagents, decrease in Na₂S content, and
541 consequently a reduction in water consumption by as much as 34.62%.

542 The biohydrometallurgical method, using post-flotation water, can recover valuable cobalt
543 (Dudeney et al., 2013; Parbhakar-Fox et al., 2018). Monitoring the quality of unused post-
544 flotation water is a very important for assessing the stability of the structure of reservoirs and
545 dams, in which these wastes are collected (Retka et al., 2020).

546 Waste management in the Oil & Gas sector largely relies on the water treatment used for
547 drilling. As a result of contact with highly saline water and the shale itself in the fracturing
548 zone, the drilling fluid is enriched with chlorides and barium salts. Contaminated water from
549 drilling works in the production of crude oil and natural gas is circulated. Very often it can be
550 reused up to 100%, for example, the United States recycles more than 90% of polluted water.
551 Contaminated water from drilling processes can be returned to the surface, cleaned with
552 vibratory screens, centrifuges, hydrocyclones, etc., and reused for further drilling purposes. It
553 is assumed that more than 90% of the flowback fluid is recycled at the well stations and used
554 for subsequent drilling processes. The rest of the polluted water is directed for disposal
555 (Steliga and Uliasz, 2012). In order to recover a significant amount of the fracturing fluid, in
556 other words flowback fluid, consisting of 90 to 95% of water and chemical additives, the fluid
557 undergoes a treatment procedure (Steliga and Uliasz, 2012).

558 The exploration and drilling site is usually protected by lining with cement slabs and foil to
559 minimize the risk of toxic compounds getting into the soil and surface waters (Dudeney et al.,
560 2013). Example of the storage sites is Łebień drilling rig which is shown in Figure VI, in the
561 appendix.

562 5.3. *The impact of waste management on the environment*

563 Metal mining is a key part of the economy for many countries. Many countries decide to
564 explore small deposits of raw materials for which the demand is growing every year. As a
565 consequence, the amount of waste produced also increases (Bamigboye et al., 2021; Nikolić
566 et al., 2019).

567 It is practically impossible to prevent the generation of post-mining waste. Tailings are
568 troublesome to handle due to their high abundance, properties, and difficulty in removal. As
569 a result, long-term processes are used to minimize negative environmental and socio-
570 economic consequences. The generated waste is either sent for recovery or neutralization,
571 wherein neutralization most often means disposal in dedicated landfills.

572 The literature review is rich in examples showing that wastes from flotation process can be
573 slightly toxic. It is confirmed by studies of plants and water that have come into contact with
574 them, therefore their storage is not the most beneficial solution because it affects the
575 environment and occupies a very large area, and also distorts the landscape (Behera et al.,
576 2020).

577 A lot of papers present research (Ciarkowska et al., 2017; Kasowska et al., 2018; Mendez and
578 Maier, 2008; Śliwka et al., 2013) in which plants, mainly trees, were planted on copper tailings
579 to examine the accumulation of metals. The aim of using plants, known as phytostabilization,
580 is to reduce the risk of metal migration to deeper soil layers. The experiments showed that
581 some plants contained a critical amount of copper, which thereby confirmed high copper
582 content in the waste, and inefficiency of the flotation process. Permissible lead levels were
583 exceeded. The obtained results showed the best accumulation properties of metals for fungi.
584 Additionally, an increased content of heavy metals, especially copper, was detected in pine
585 needles.

586 Jakovjević K. and Mišlejenović et al. 2020 (Jakovljević et al., 2020), carried out a study to
587 determine the toxicity level of plants growing in 4 soil samples taken from different parts of
588 the post-flotation tank. The highest concentration of toxic elements (As, Sb, Zn) was
589 determined in samples from the vicinity of the closed Stolice mine in Serbia (Zn-Pb
590 polymetallic deposit, a flotation basin), and from Zn-Pb tailings near the Ibar River. Even
591 though the mine was closed in 1987, it still poses a threat. The waste that was generated still
592 contains potentially toxic elements. The greatest accumulation of these elements is near the
593 river; therefore, they can potentially get there, polluting the river and aquatic organisms.

594 On the other hand, a water study carried out at the closed Jerada mine in Morocco, where 15
595 to 20 million tons of waste is currently stored, showed an increase in sulphate content to over
596 700 mg/l, with an average level of around 300 mg/l. The increase was observed during the
597 rainy season, indicating that surface water migration has an impact on pollution levels.

598 Studies of the abandoned tailings from a mine in Mexico, revealed that the oxidation of
599 chemicals was less intense in the settling tank than in the dam. The pH was low in the oxidized
600 zone (down to 2.7), and was increasing with the depth, indicating that the H⁺ ions are
601 consumed by dissolving the aluminosilicate minerals. This results in the precipitation of iron
602 oxides which in the presence of form cement layers in the dam. The waste contained high
603 level of heavy metals easily washed away by water (As and SO₄²⁻). The concentration and
604 mobility of the toxic elements is controlled by precipitation, sorption and desorption (Romero
605 et al., 2007). In studies on the toxicity of tailings from mines in Norway, it was concluded that
606 tailings from a mine, where no process chemicals were used, had the greatest toxicity. This
607 means that properly selected chemicals in the flotation process is a very important factor that
608 can minimize the toxicity of a generated waste (Brooks et al., 2019) It was also shown that the
609 ion exchange process can be effective in purifying water after the zinc and lead ore flotation
610 process (Woynarowska et al., 2011).

611 Being aware of the risk to the environment coming from generated waste and landfilled
612 tailings, more effective methods are needed to reduce negative impacts on air, soil, and
613 water. It is a challenge; hence the role of innovation is very crucial here. It is important to
614 protect the waste from migration and to ensure the geotechnical stability of disposal site. In
615 order to reduce the impact of waste on the environment, various techniques are applied,



616 among others physical methods that create a barrier to the migration of pollutants, e.g.
617 geotextile separators - functioning as barrier between the ground and the stored waste, multi-
618 layer coverings - protecting from external weather conditions, or the aforementioned
619 biological methods, like phytostabilization or hydroseeding, in which a mixture of fertilizer,
620 seeds and water is sprayed onto the ground to make the grass grow. It is important to protect
621 the waste from migration and to ensure the geotechnical stability of disposal site (González-
622 Alday et al., 2008; Karczewska et al., 2017).

623 Additionally, to provide support for environmental protection legal regulations are applied. In
624 the EU, European Commission has introduced directives related to waste management, which
625 among others regulate waste from extractive industries (Directive 2006/21/EC), control of
626 major-accident hazards involving dangerous substances (Directive 2012/18/EU) and
627 protection of groundwater against pollution and deterioration (Directive 2006/118/EC).
628 Additionally, in accordance with Directive 2006/21/EC, Joint Research Centre provided Best
629 Available Techniques Reference Document for the Management of Waste from Extractive
630 Industries (MWEI BREF) (Garbarino et al., 2018). MWEI-BREF, which is a technical document,
631 aimed at minimizing the environmental impact connected with extraction of mineral
632 resources, includes among others generic and risk-specific BAT conclusions, generic and risk-
633 specific objectives, information about management, as well as emerging techniques to
634 prevent environmental deterioration coming from extractive industry (Garbarino et al., 2020).

635 Extraction of resources, which is inherent in the production of waste, to ensure short-term
636 and long-term safety, requires following a predetermined plan, considering life cycle
637 assessment, risk assessment, and waste deposition plan so to minimize the adverse effects on
638 the environment and eventually human health. Additionally, it should also include a planning
639 for closure of extraction and disposal facility, including rehabilitation, reclamation,
640 remediation, after-closure procedures, and subsequent monitoring (Garbarino et al., 2018).

641 **6. New methods of waste management**

642 *6.1. Copper, zinc and lead*

643 The potential of the use of tailings has been discussed for many years. Already in 1996, an
644 article was published on the possibility of using mining and energy waste in the construction
645 of expressways and highways (Kozioł and Uberman, 1996). It was found that waste from rock
646 mining can be used as a road aggregate for the construction of road foundation.

647 Due to the chemical and phase composition, the most frequently considered solution for the
648 management of tailings, other than neutralization in tanks, is using it as an additive to cement
649 (Gao et al., 2020; Gou et al., 2019; Guo et al., 2016; Liu et al., 2018; Muravyov et al., 2012;
650 Onuaguluchi and Eren, 2012; Wang et al., 2017; Yi and Cao, 2014; Zheng et al., 2015).
651 According to the European standard (*EN 197-1:2012. Cement. Part 1: Composition,
652 specifications and conformity for common cements, European Standards.*, 2012), additives
653 added in the amount of up to 40% of the cement mass improve some functional properties.

654 The greatest economic benefit resulting from the use of flotation waste in the building
655 materials industry is the saving of cement, which can be replaced by waste, even in a small
656 percentage (Mikula et al., 2021).

657 Chinese scientists (Guo et al., 2016) checked the pozzolanic activity of tailings generated in
658 the process of pyrite flotation. An X-ray fluorescence analysis was performed to identify the
659 main components of the waste. Pozzolanic materials are characterized by a high content of
660 SiO_2 and Al_2O_3 . This was also in the case of examined waste, which additionally contained
661 small amounts of alkali. The optimal amount of waste was determined at the level of 20% of
662 the cement mass. This amount of waste causes that the concrete has still good workability.

663 Coal tailings can also be used as pozzolanic material. This was shown in the research: (Yagüe
664 et al., 2018). Very fine samples had the best properties, however they required thermal
665 activation treatment (Qiu et al., 2011).

666 The use of dry copper tailings may increase the yield point, which is an undesirable effect,
667 however the use of pre-moistened waste has reduced this disadvantage. The samples showed
668 a higher initial water absorption rate and resistance to chloride penetration and acids
669 (Onuaguluchi and Eren, 2012).

670 Concrete mixes with the addition of tailings are characterized by water resistance and better
671 hydrophobicity than traditional cement mortar (Liu et al., 2017). The addition of tailings from
672 reverse flotation can significantly improve the watertightness of cement mortars. The mixture
673 prepared for self-compacting concrete showed high resistance to freezing and thawing, and it
674 can be classified as XF4 concrete exposure class. Scientists from the University of Nis (Ristić et
675 al., 2019) showed that the addition of copper tailings, in the amount of about 40% of the
676 cement mass, did not significantly affect such parameters as air content or segregation.


677 Low air content and high bulk density are more suitable for laying bricks (Fontes et al., 2016).
678 The composite made of zinc and lead tailings and fly ash is a good solution for backfilling
679 workings, however appropriate proportions of mixtures need to be kept, preventing their
680 secondary liquefaction (Jarosiński et al., 2007; Jarosiński and Madejska, 2008).

681 Alexander Karamanov et al. (Karamanov et al., 2007) investigated the use of flotation waste
682 as an ingredient in the production of glass-ceramics. They found that flotation wastes alone
683 are not enough to create high-quality glass, and mixes with various additives are better. No
684 visible air bubbles were observed in the obtained glasses. After thermal treatment, the
685 material became homogeneous, which increased its strength. The grinding made the material
686 similar in texture to granite.

687 Another example of using tailings is building ceramics. Mymrin V. (2020) et al. (Mymrin et al.,
688 2020) created mixtures containing lead ore flotation tailings, foundry sand and a mixture of
689 sand and clay. The 10% addition of waste increased the compressive strength by 8%. The SEM
690 images showed the formation of a new amorphous glassy phase that covered all surfaces of
691 the ceramics and closed the porous space, thus strengthening the samples (Alekseev et al.,

692 2019; Bhardwaj and Kumar, 2019; Hossiney et al., 2018; Mackay et al., 2020; Sua-iam et al.,
693 2019).

694 Applying even a small amount of tailings to concrete is beneficial since it reduces
695 environmental impact and contribute to land remediation (Onuaguluchi and Eren, 2012).
696 Summary of advantages and disadvantages of using flotation waste as building materials is
697 presented in figure 19.



698

699 **Figure 19.** Summary of advantages and disadvantages of using flotation waste as building
700 materials

701 Flotation waste is also used to recover many valuable elements. There are many studies and
702 publications showing that the elements copper, zinc, lead and can be obtained from waste.
703 However, these processes also generate wastes that are even more difficult to handle. These
704 wastes are free of key elements and contain foaming additives and chemical solvents. Over
705 the years, the amount of exploited metal, coal, oil and gas deposits decreases, hence it is
706 expected that the flotation process will be even more effective, and thus the post-flotation
707 waste will have a different chemical composition, less harmful to the environment. Reducing
708 the number of deposits and extraction from deposits of lower quality will contribute to an
709 increase in the amount of waste.

710 6.2. Oil and gas extraction

711 Historically, a number of non-biological methods have been used to remove drill cuttings,
712 including backfilling pits, landfills and reinjection wells, chemical stabilization and
713 solidification, as well as thermal treatments such as incineration and thermal desorption. The
714 results of the research showed that drilling waste that is not classified as hazardous, due to its
715 high pH, could be used for the remediation of land degraded by acidification, e.g. located in

716 the vicinity of open pit sulfur mines or on heaps of mining waste containing acid minerals, e.g.
717 pyrite (Ball et al., 2012) The confirmation of such development is also presented by Kujawska
718 et al. (2020) (Kujawska and Pawłowska, 2020), proposing the remediation of acidic, barren
719 and degraded soils. Another example is the use of the drill cuttings as construction aggregate,
720 the formation of granules or burning and creating a natural fertilizer for plants.

721 Depending on properties, solid waste, cleaned from oily substances, can be used in
722 construction. Leonard et al. (Leonard and Stegemann, 2010) presented the possibility of using
723 two types of waste to produce Portland Cement (CEM I). One component were the stabilized
724 and solidified drill cuttings and the second was the residue from coal combustion, i.e., fly ash
725 with high carbon content as additional component of organic pollutants.

726 Another type of drill cuttings is from the oil sands in Canada and represents one of the most
727 difficult challenges for the mining sector. Oil sands are cleaned using the so-called Thermo-
728 Mechanical Cuttings Cleaner. The waste is heated to a temperature high enough to evaporate
729 the oil and water, which are then transferred to the liquid phase in separate condensers. The
730 by-product is a very fine quartz powder that can potentially be used as a filler material in the
731 production of cement materials (Aboutabikh et al., 2016; Boudens et al., 2016; Huang et al.,
732 2015; Loganathan et al., 2015).

733 **7. Results and discussion**

734 A review of the world literature shows increasing interest in a mining waste management.
735 Innovative solutions are constantly searched for, which will allow waste management not only
736 through storage, but also efficient use, striving to reduce CO₂ emissions and improving the
737 quality of environment. Table 2 summarizes methods of managing individual types of waste,
738 indicating the numerous possibilities of post-flotation and mining waste management.

739 **Table 2.** Waste management options according to waste characteristics

Source	Type of waste	Parameters	Method of waste management	References	
Copper	Waste rock and overburden	<ul style="list-style-type: none"> - Compressive strength [MPa] - Chemical composition [%] - Graining [%] - Water absorption [%] 	<ul style="list-style-type: none"> • aggregate in concrete and road construction • the backfilling of mined headings/workings and post-mining voids as a material for dry filling, • the backfilling of the voids that were formed as a result of mining as the material for supplemental sealing • the backfilling of the headings that require strengthening and stabilisation • the hardening of underground mine roads • source recovery • recovery of chemical elements 	(Henne et al., 2018; Kotarska et al., 2018; Lidelöw et al., 2017; Rossetti et al., 2019)	
	Flotation Tailings	<ul style="list-style-type: none"> - Chemical composition [%] 	<ul style="list-style-type: none"> • chemical precipitation • reuse of water in the flotation process 	<ul style="list-style-type: none"> • purification of water from metals and sulfates • for the production of mineral binder 	(Nariyan et al., 2017; Rajczyk, 2017; Shengo and Mutiti, 2016)
	Smelter and tailing slag	<ul style="list-style-type: none"> - Compressive and flexural strength [MPa] - Chemical composition [%] - Graining [%] - Friction [N] - Water absorption [%] 	<ul style="list-style-type: none"> • aggregate in concrete and road construction • source recovery • for the production of mineral binder 	<ul style="list-style-type: none"> • the hardening of underground mine roads • reaction catalyst 	(Esmaeili and Aslani, 2019; Kiventerä et al., 2020; Li et al., 2018; Mikula et al., 2021; Muleya et al., 2020; Nikolić et al., 2019; Paiva et al., 2019)
inc	Flotation waste	<ul style="list-style-type: none"> - Compressive strength [MPa] - Chemical composition [%] - Water absorption [%] 	<ul style="list-style-type: none"> • as proppant • reuse of water in the flotation process 	<ul style="list-style-type: none"> • source recovery • hydrophobic surface 	(Azevedo et al., 2018; Muravyov and Fomchenko, 2018; Pietrzykowski et al., 2018; Wang et al., 2017)
	Waste water	<ul style="list-style-type: none"> - Chemical composition [%] 	<ul style="list-style-type: none"> • reuse of water in the flotation process 		(Azevedo et al., 2018; Kyzas and Matis, 2019)



Lead	Flotation waste	<ul style="list-style-type: none"> - Compressive strength [MPa] - Chemical composition [%] - Water absorption [%] 	<ul style="list-style-type: none"> • as proppant • as a component of the ceramics industry roofing material 	<ul style="list-style-type: none"> • source recovery 	(Kudeřko, 2018; Larachi et al., 2019; Romero-García et al., 2019; Woźniak and Pactwa, 2018)
	Waste water	<ul style="list-style-type: none"> - Chemical composition [%] 	<ul style="list-style-type: none"> • coagulation with the application of lime carbide residue 	<ul style="list-style-type: none"> • reuse of water in the flotation process 	(Azevedo et al., 2018; Kyzas and Matis, 2019)
Coal	Flotation coal enrichment	<ul style="list-style-type: none"> - Chemical composition [%] 	<ul style="list-style-type: none"> • flooring 		(Gupta et al., 2017; Wang et al., 2020)
	Bottom ash	<ul style="list-style-type: none"> - Compressive strength [MPa] - Chemical composition [%] - Graining [%] - Water absorption [%] 	<ul style="list-style-type: none"> • incinerating/fertilizer for plants • the backfilling of the voids that were formed as a result of mining as the material for supplemental sealing 	<ul style="list-style-type: none"> • ceramics materials • phosphorus adsorbent • aggregate 	(Muthusamy et al., 2020; Namkane et al., 2017; Rani and Jain, 2017; Zhou et al., 2019)
Oil & Gas	Cuttings, Sludges waste, Scales waste	<ul style="list-style-type: none"> - Compressive and flexural strength [MPa] - Graining [%] - Water absorption [%] 	<ul style="list-style-type: none"> • land application and landfilling • discharge to surface • recycling • as proppant/road construction 	<ul style="list-style-type: none"> • incinerating/fertilizer for plants • aggregate • surface of tennis courts 	(Ayati et al., 2019; Davarpanah et al., 2018; de Almeida et al., 2017; Hu et al., 2021; Hussain et al., 2017; Reuben et al., 2018; Stuckman et al., 2018)
	Waste water	<ul style="list-style-type: none"> - Chemical composition [%] 	<ul style="list-style-type: none"> • surface impoundment • underground injection • waters source reduction • simple and enhanced separation 	<ul style="list-style-type: none"> • dissolved air flotation • evaporative treatment • deep well • recovery water to the process 	(Abdullah et al., 2017; Adham et al., 2018; Robbins et al., 2020)

741 The article presents many advantages and additional possibilities of using flotation tailings as
742 a partial replacement of aggregate or cement. However, one of the biggest disadvantages of
743 post-mining waste is its chemical and thus mineralogical variability. Flotation tailings differ in
744 their chemical composition, depending on the mined ores or whether oil or gas is being
745 extracted. The waste may contain trace amounts of elements that may adversely affect the
746 concrete structure, such as sulphur and iron compounds, as well as heavy metals.

747 Another issue to replace the materials used in the production of concrete is the fact that
748 concrete plants and cement plants have a developed, proven system and do not necessarily
749 want to retrain to new solutions.

750 In the past, the flotation waste, due to transportation problems and no development
751 directions, was deposited in earth settlements, which degraded the natural environment,
752 disfigured the landscape and increased the areas transformed by mining activities. Such
753 approach led to environmental damage and exposed mines to huge losses due to waste of
754 raw materials and fees for land use, etc. (Alwaeli M., 2009).

755 The biggest problem when using waste as components of building materials is the need to
756 prepare the waste for use (Dash et al., 2016). Usually, the material should be additionally
757 shredded or roasted (Kotwica et al., 2018). In order for the waste to be used effectively as an
758 additive to building materials, additives are used such as alkaline activators (Ahmari et al.,
759 2015). This means introducing additional chemical ingredients into the materials. All the
760 above-mentioned activities generate costs related to the processing of waste so that it can be
761 used.

762 Another common problem in the use of waste as components of building materials is the
763 change in physical parameters of the material. With the use of waste, a decrease in strength
764 (caused by the problem with the formation of appropriate tricalcium aluminates, silicates) and
765 there are noted a decrease in the workability of concrete (high absorbability of e.g., ash)
766 (Capasso et al., 2019). Another problem is the reduction of adhesion or discoloration of the
767 material (e.g. in ceramic tiles, glaze layers cannot be applied) (Rahman et al., 2020).

768 When considering the use of waste in the building materials industry, in chemical aspects,
769 there is a problem with heavy metals and their potential leachability from finished products
770 (Dell'Orso et al., 2012). However, there are studies and publications (Yu et al., 2005) that show
771 that cement materials do not leach dangerous amounts of heavy metals, because they have
772 been incorporated into the structure of the hardened composite.

773 The last threat arising from the use of waste in the building materials industry is the law and
774 standards. For safety reasons, European standards for cement, concrete and other building
775 materials are very strict. Therefore, the condition of waste and finished building elements
776 should be properly examined and monitored so that their use does not turn out to be harmful
777 and dangerous, as it turned out in the case of asbestos.

778 To summarize the risks of using waste in the building materials industry, there are many
779 obstacles and a financial effort is needed to prepare the waste for use in construction.
780 However, as shown in the article, there are many more advantages and positive aspects to
781 continue developing the waste utilization processes.

782 **8. Conclusions**

783 Mining is still a key part of the economy for many countries, and it is practically impossible to
784 prevent the generation of post-mining waste. That is why in this work authors selected the
785 most key resources in the mining industry, which are metals ores, coal, oil and natural gas,
786 and focused on best solution for the generated waste to be safely managed or re-used. The
787 proposed methods for handling with produced waste present both benefits and
788 disadvantages, and additionally include environmental aspects that conditions a more
789 sustainable waste management.

790 Mining wastes are high in abundance, properties, and difficult in removal. The generated
791 waste is very often sent for recovery or neutralization, wherein neutralization most often
792 means disposal in dedicated landfills, which is ground storage in waste neutralization tanks.
793 Currently, this is the most popular method of post-flotation waste management, even though
794 it is known that continuous collection of massive amounts of wastes may eventually result in
795 disastrous environmental degradation. The waste, especially those untreated, may contain
796 toxic and harmful elements, hence it is important to store it far from rivers and farmlands to
797 minimize the risk of pollution of rivers and soils as well as groundwaters. However, it is not
798 only storing and possibility of leakage to the ground, which pose a threat to the surrounding
799 area, but also the ash that may be released from the storage tanks, which very often are not
800 well covered. Some additional risk may arise, when wastes like for example drill-cuttings need
801 to be pre-treated, which will involve additional waste generating processes.

802 Since the current waste management in the mining industry is very often far from being
803 sustainable, this paper includes an overview of waste management practices that are more
804 environmentally friendly and presents alternative methods of waste management. At the
805 same time, this review covers data on properties and composition of mining and processing
806 waste, aiming at identifying the unused benefits of improper waste management and
807 handling.

808 Environmental concerns related to the management of mining waste are growing every year,
809 which eventually leads to the need to recycling and reusing this waste. Due to the
810 characteristic chemical composition, as shown in this article, the recycling of post-flotation
811 and mining waste has the potential to be used in the building materials. Innovative solutions
812 are constantly searched for, which will allow waste management not only through storage,
813 but also efficient use, striving to reduce CO₂ emissions and improving the quality of
814 environment.

815 The article contains a detailed review of the literature on geology and the current
816 management of by-products generated in the processes of extraction and processing of raw
817 materials. The amounts, chemical compositions, and forms of occurrence of metal ores of
818 copper, zinc, lead, as well as coal, crude oil and natural gas deposits are discussed in detail.
819 Waste management methods and their potential possibilities are presented and discussed.

820 Based on the literature results, new waste management options are proposed, which consider
821 the recycling of already stored material and waste generated from current production. It has
822 been shown that the current management of the above-mentioned waste, by depositing it in
823 waste disposal facilities, is one of the less effective activities, and has negative impact on the
824 environment, especially in a case of surroundings of the tanks.

825 A deeper look into the conditions and possibilities of waste management may result in
826 drawing the attention of specialists in the fields of environmental protection and the building
827 materials encouraging them to the use by-products from mining processes. The greater the
828 knowledge about the possibilities of using post-flotation waste, the more effective the
829 solutions to meet today's challenges.

830 **References**

- 831 Abdullah, K., Stenstrom, M., Suffet, I.H. (Mel., Swamikannu, X., Malloy, T., 2017. Regulating oil
832 and gas facility stormwater discharge: An assessment of surface impoundments, spills,
833 and permit compliance. *Environ. Sci. Policy* 76, 139–145.
834 <https://doi.org/10.1016/j.envsci.2017.06.016>
- 835 Aboutabikh, M., Soliman, A.M., El Naggar, M.H., 2016. Properties of cementitious material
836 incorporating treated oil sands drill cuttings waste. *Constr. Build. Mater.* 111, 751–757.
837 <https://doi.org/10.1016/j.conbuildmat.2016.02.163>
- 838 Abu-Hamatteh, Z.S.H., Al-Amr, A.M., 2008. Carnallite froth flotation optimization and cell
839 efficiency in the arab potash company, Dead Sea, Jordan. *Miner. Process. Extr. Metall.*
840 *Rev.* 29, 232–257. <https://doi.org/10.1080/08827500801997894>
- 841 Adham, S., Hussain, A., Minier-Matar, J., Janson, A., Sharma, R., 2018. Membrane applications
842 and opportunities for water management in the oil & gas industry. *Desalination* 440, 2–
843 17. <https://doi.org/10.1016/j.desal.2018.01.030>
- 844 Ahmari, S., Parameswaran, K., Zhang, L., 2015. Alkali Activation of Copper Mine Tailings and
845 Low-Calcium Flash-Furnace Copper Smelter Slag. *J. Mater. Civ. Eng.* 27, 04014193.
846 [https://doi.org/10.1061/\(asce\)mt.1943-5533.0001159](https://doi.org/10.1061/(asce)mt.1943-5533.0001159)
- 847 Alekseev, K., Mymrin, V., Avanci, M.A., Klitzke, W., Magalhães, W.L.E., Silva, P.R., Catai, R.E.,
848 Silva, D.A., Ferraz, F.A., 2019. Environmentally clean construction materials from
849 hazardous bauxite waste red mud and spent foundry sand. *Constr. Build. Mater.* 229,
850 116860. <https://doi.org/10.1016/j.conbuildmat.2019.116860>
- 851 Alp, I., Deveci, H., Süngün, H., 2008. Utilization of flotation wastes of copper slag as raw
852 material in cement production. *J. Hazard. Mater.* 159, 390–395.
853 <https://doi.org/10.1016/j.jhazmat.2008.02.056>
- 854 Alwaeli M., C.Ł., 2009. Możliwości gospodarczegow wykorzystania odpadow poflotacyjnych.
855 *Arch. Gospod. Odpad. i Ochr. środowiska* 11, 47–62.
- 856 Amy C. Tolcin, 2020. *Mineral Commodity Summaries* 190–191.
- 857 Announcement of the Marshal of the Sejm of the Republic of Poland of October 8, 2020 on
858 the publication of the uniform text of the Act on mining waste, *Dz. U.* 2020, pos. 2018,
859 2020.
- 860 Asadi, T., Azizi, A., Lee, J.C., Jahani, M., 2017. Leaching of zinc from a lead-zinc flotation tailing
861 sample using ferric sulphate and sulfuric acid media. *J. Environ. Chem. Eng.* 5, 4769–4775.
862 <https://doi.org/10.1016/j.jece.2017.09.005>
- 863 Ayati, B., Molineux, C., Newport, D., Cheeseman, C., 2019. Manufacture and performance of
864 lightweight aggregate from waste drill cuttings. *J. Clean. Prod.* 208, 252–260.
865 <https://doi.org/10.1016/j.jclepro.2018.10.134>
- 866 Azevedo, A., Oliveira, H.A., Rubio, J., 2018. Treatment and water reuse of lead-zinc sulphide
867 ore mill wastewaters by high rate dissolved air flotation. *Miner. Eng.* 127, 114–121.
868 <https://doi.org/10.1016/j.mineng.2018.07.011>

- 869 Baic, I., Witkowska-Kita, B., 2011. Technologie zagospodarowania odpadów z górnictwa węgla
870 kamiennego - diagnoza stanu aktualnego, ocena innowacyjności i analiza swot. Roczn.
871 Ochr. Sr. 13, 1315–1326.
- 872 Bakalarz, A., 2019. Chemical and Mineral Analysis of Flotation Tailings from Stratiform Copper
873 Ore from Lubin Concentrator Plant (SW Poland). Miner. Process. Extr. Metall. Rev. 40,
874 437–446. <https://doi.org/10.1080/08827508.2019.1667778>
- 875 Ball, A.S., Stewart, R.J., Schliephake, K., 2012. A review of the current options for the treatment
876 and safe disposal of drill cuttings. Waste Manag. Res. 30, 457–473.
877 <https://doi.org/10.1177/0734242X11419892>
- 878 Bamigboye, G.O., Basse, D.E., Olukanni, D.O., Ngene, B.U., Adegoke, D., Odetoyan, A.O.,
879 Kareem, M.A., Enabulele, D.O., Nworgu, A.T., 2021. Waste materials in highway
880 applications: An overview on generation and utilization implications on sustainability. J.
881 Clean. Prod. 283, 124581. <https://doi.org/10.1016/j.jclepro.2020.124581>
- 882 Behera, S.K., Ghosh, C.N., Mishra, K., Mishra, D.P., Singh, P., Mandal, P.K., Buragohain, J., Sethi,
883 M.K., 2020. Utilisation of lead–zinc mill tailings and slag as paste backfill materials.
884 Environ. Earth Sci. 79, 1–18. <https://doi.org/10.1007/s12665-020-09132-x>
- 885 Bhardwaj, B., Kumar, P., 2019. Comparative study of geopolymer and alkali activated slag
886 concrete comprising waste foundry sand. Constr. Build. Mater. 209, 555–565.
887 <https://doi.org/10.1016/j.conbuildmat.2019.03.107>
- 888 Biernacka, J., Borysiuk, K., Raczynski, P., 2005. Zechstein (Ca1) limestone-marl alternations
889 from the North-Sudetic Basin, Poland: Depositional or diagenetic rhythms? Geol. Q. 49,
890 1–14.
- 891 Boudens, R., Reid, T., VanMensel, D., Sabari Prakasan, M.R., Ciborowski, J.J.H., Weisener, C.G.,
892 2016. Bio-physicochemical effects of gamma irradiation treatment for naphthenic acids
893 in oil sands fluid fine tailings. Sci. Total Environ. 539, 114–124.
894 <https://doi.org/10.1016/j.scitotenv.2015.08.125>
- 895 Bouguermouh, K., Bouzidi, N., Mahtout, L., Hassam, T., Mouhoub, S., Pérez-Villarejo, L., 2018.
896 Stabilization of flotation wastes resulting from the treatment of Pb/Zn ore based on
897 geopolymers. Mater. Lett. 227, 221–224. <https://doi.org/10.1016/j.matlet.2018.05.089>
- 898 bp Statistical Review of World Energy [WWW Document], 2020. URL
899 [https://www.bp.com/content/dam/bp/business-](https://www.bp.com/content/dam/bp/business-sites/en/global/corporate/pdfs/energy-economics/statistical-review/bp-stats-review-2020-full-report.pdf)
900 [sites/en/global/corporate/pdfs/energy-economics/statistical-review/bp-stats-review-](https://www.bp.com/content/dam/bp/business-sites/en/global/corporate/pdfs/energy-economics/statistical-review/bp-stats-review-2020-full-report.pdf)
901 [2020-full-report.pdf](https://www.bp.com/content/dam/bp/business-sites/en/global/corporate/pdfs/energy-economics/statistical-review/bp-stats-review-2020-full-report.pdf) (accessed 1.14.21).
- 902 British Petroleum, 2010. Deepwater Horizon Accident Investigation Report. Intern. BP Rep. 22.
- 903 Brooks, S.J., Escudero-Oñate, C., Lillicrap, A.D., 2019. An ecotoxicological assessment of mine
904 tailings from three Norwegian mines. Chemosphere 233, 818–827.
905 <https://doi.org/10.1016/j.chemosphere.2019.06.003>
- 906 Brown, T.J., Idoine, N.E., Wrighton, C.E., Raycraft, E.R., Hobbs, S.F., Shaw, R.A., Everett, P.,
907 Kresse, C., Deady, E.A., Bide, T., 2020. WORLD MINERAL PRODUCTION, World Mineral
908 Production 2014-18. <https://doi.org/10.1017/CBO9780511763175.034>

- 909 Cabała, J., 2010. Cynk w technosferze. *Górnictwo i Geol.* 5, 63–76.
- 910 Capasso, I., Lirer, S., Flora, A., Ferone, C., Cioffi, R., Caputo, D., Liguori, B., 2019. Reuse of
911 mining waste as aggregates in fly ash-based geopolymers. *J. Clean. Prod.* 220, 65–73.
912 <https://doi.org/10.1016/j.jclepro.2019.02.164>
- 913 Chen, G., Xia, B., Wu, Y., Tu, G., Yu, H., 2000. The metallogenic mechanism of the sandstone-
914 type copper deposits in the Chuxiong Basin, Yunnan Province. *Sci. China, Ser. D Earth Sci.*
915 43, 263–272. <https://doi.org/10.1007/bf02911951>
- 916 Ciarkowska, K., Hanus-Fajerska, E., 2008. Remediation of Soil-Free grounds contaminated by
917 Zinc, Lead and Cadmium with the use of Metanophytes. *Polish J. Environ. Stud.* 17, 707–
918 712.
- 919 Ciarkowska, K., Hanus-Fajerska, E., Gambuś, F., Muszyńska, E., Czech, T., 2017.
920 Phytostabilization of Zn-Pb ore flotation tailings with *Dianthus carthusianorum* and
921 *Biscutella laevigata* after amending with mineral fertilizers or sewage sludge. *J. Environ.*
922 *Manage.* 189, 75–83. <https://doi.org/10.1016/j.jenvman.2016.12.028>
- 923 Coal and lignite production [WWW Document], 2019. URL
924 <https://yearbook.enerdata.net/coal-lignite/coal-production-data.html> (accessed
925 1.14.21).
- 926 Copper alliance [WWW Document], 2018. URL [https://copperalliance.pl/baza-
927 wiedzy/edukacja/miedz-wlasciwosci-zastosowania](https://copperalliance.pl/baza-wiedzy/edukacja/miedz-wlasciwosci-zastosowania) (accessed 1.14.21).
- 928 Çoruh, S., Elevli, S., Geyikçi, F., 2012. Statistical evaluation and optimization of factors affecting
929 the leaching performance of copper flotation waste. *Sci. World J.* 2012.
930 <https://doi.org/10.1100/2012/758719>
- 931 Çoruh, S., Ergun, O.N., 2006. Leaching characteristics of copper flotation waste before and
932 after vitrification. *J. Environ. Manage.* 81, 333–338.
933 <https://doi.org/10.1016/j.jenvman.2005.11.006>
- 934 Crude oil production [WWW Document], 2019. URL [https://yearbook.enerdata.net/crude-
935 oil/world-production-statistics.html](https://yearbook.enerdata.net/crude-oil/world-production-statistics.html)
- 936 Daldoul, G., Souissi, R., Tlili, H., Elbahri, D., El Hamiani, O., Chebbi, N., Boularbah, A., Souissi, F.,
937 2019. Assessment of heavy metal toxicity in soils contaminated by a former Pb–Zn mine
938 and tailings management using flotation process, Jebel Ghazlane, Northern Tunisia.
939 *Environ. Earth Sci.* 78, 1–14. <https://doi.org/10.1007/s12665-019-8720-3>
- 940 Dash, M.K., Patro, S.K., Rath, A.K., 2016. Sustainable use of industrial-waste as partial
941 replacement of fine aggregate for preparation of concrete – A review. *Int. J. Sustain. Built*
942 *Environ.* 5, 484–516. <https://doi.org/10.1016/j.ijbsbe.2016.04.006>
- 943 Davarpanah, A., Razmjoo, A., Mirshekari, B., Fantke, P., 2018. An overview of management,
944 recycling, and wasting disposal in the drilling operation of oil and gas wells in Iran. *Cogent*
945 *Environ. Sci.* 4, 1537066. <https://doi.org/10.1080/23311843.2018.1537066>
- 946 de Almeida, P.C., Araújo, O. de Q.F., de Medeiros, J.L., 2017. Managing offshore drill cuttings
947 waste for improved sustainability. *J. Clean. Prod.* 165, 143–156.
948 <https://doi.org/10.1016/j.jclepro.2017.07.062>

- 949 Dell'Orso, M., Mangialardi, T., Paolini, A.E., Piga, L., 2012. Evaluation of the leachability of
 950 heavy metals from cement-based materials. *J. Hazard. Mater.* 227–228, 1–8.
 951 <https://doi.org/10.1016/j.jhazmat.2012.04.017>
- 952 Dice, M.E., 2017. A Regional Study Of Wilcox Reservoirs In The Deepwater Northern Gulf Of
 953 Mexico.
- 954 Drachev, S.S., Malyshev, N.A., Nikishin, A.M., 2010. Tectonic history and petroleum geology of
 955 the Russian Arctic Shelves: An overview. *Pet. Geol. Conf. Proc.* 7, 591–619.
 956 <https://doi.org/10.1144/0070591>
- 957 Dudeney, A.W.L., Chan, B.K.C., Bouzalakos, S., Huisman, J.L., 2013. Management of waste and
 958 wastewater from mineral industry processes, especially leaching of sulphide resources:
 959 State of the art. *Int. J. Mining, Reclam. Environ.* 27, 2–37.
 960 <https://doi.org/10.1080/17480930.2012.696790>
- 961 Eldridge, R.B., 1996. Oil contaminant removal from drill cuttings by supercritical extraction.
 962 *Ind. Eng. Chem. Res.* 35, 1901–1905. <https://doi.org/10.1021/ie950765t>
- 963 EN 197-1:2012. Cement. Part 1: Composition, specifications and conformity for common
 964 cements, European Standards., 2012. . Brussels, Belgium.
- 965 Esmaeili, J., Aslani, H., 2019. Use of copper mine tailing in concrete: strength characteristics
 966 and durability performance. *J. Mater. Cycles Waste Manag.* 21, 729–741.
 967 <https://doi.org/10.1007/s10163-019-00831-7>
- 968 Europejski, P., Unii, I.R., 2006. Dyrektywa 2006/21/WE Parlamentu Europejskiego i Rady z dnia
 969 15 marca 2006 r. w sprawie gospodarowania odpadami pochodzącymi z przemysłu
 970 wydobywczego oraz zmieniająca dyrektywę 2004/35/WE L 102/15, 64–85.
- 971 Fang, F., Han, H., Zhao, Q., Xu, C., Zhang, L., 2013. Bioaugmentation of biological contact
 972 oxidation reactor (BCOR) with phenol-degrading bacteria for coal gasification wastewater
 973 (CGW) treatment. *Bioresour. Technol.* 150, 314–320.
 974 <https://doi.org/10.1016/j.biortech.2013.09.119>
- 975 Farrokhpay, S., Zanin, M., 2012. An investigation into the effect of water quality on froth
 976 stability. *Adv. Powder Technol.* 23, 493–497. <https://doi.org/10.1016/j.apt.2012.04.012>
- 977 Fečko, P., Tora, B., Tod, M., 2013. Coal waste: Handling, pollution impacts and utilization, The
 978 Coal Handbook: Towards Cleaner Production. Woodhead Publishing Limited.
 979 <https://doi.org/10.1533/9781782421177.1.63>
- 980 Flanagan, D.M., 2019. Mineral Commodity Summaries, February 2019:Copper. *U.S. Geol. Surv.*
 981 *Miner. Commod. Summ.* 26, 101.
- 982 Fontes, W.C., Mendes, J.C., Da Silva, S.N., Peixoto, R.A.F., 2016. Mortars for laying and coating
 983 produced with iron ore tailings from tailing dams. *Constr. Build. Mater.* 112, 988–995.
 984 <https://doi.org/10.1016/j.conbuildmat.2016.03.027>
- 985 Gałkiewicz, T., Śliwiński, S., 1983. Charakterystyka geologiczna śląsko - krakowskich złóż
 986 cynkowo – ołowionych (Geological characteristics of the Silesian-Cracovian zinc-lead ore
 987 deposits). *Ann. Soc. Geol. Pol.* 53, 63–90.
- 988 Galos, K., Szlugaj, J., 2014. Gospodarka odpadami z górnictwa i przeróbki węgla kamiennego

- 989 w Polsce. *Gospod. Surowcami Miner. / Miner. Resour. Manag.* 30, 51–64.
990 <https://doi.org/10.2478/gospo-2014-0039>
- 991 Galos, K.A., Szlugaj, J., 2010. Skąły przywęglowe w górnictwie węgla kamiennego - odpady czy
992 kopaliny towarzyszące? / Barren sedimentary rocks in the hard coal mining - wastes or
993 accompanying minerals? *Górnictwo Odkryw.* 25–31.
- 994 Gao, S., Cui, X., Zhang, S., 2020. Utilization of molybdenum tailings in concrete manufacturing:
995 A review. *Appl. Sci.* 10. <https://doi.org/10.3390/app10010138>
- 996 Garbarino, E., Orveillon, G., ... H.S.-J.S. for, 2018, undefined, 2018. Best available techniques
997 (BAT) reference document for the management of waste from extractive industries,
998 Researchgate.Net. <https://doi.org/10.2760/35297>
- 999 Garbarino, E., Orveillon, G., Saveyn, H.G.M., 2020. Management of waste from extractive
1000 industries: The new European reference document on the Best Available Techniques.
1001 *Resour. Policy* 69, 101782. <https://doi.org/10.1016/j.resourpol.2020.101782>
- 1002 González-Alday, J., Marrs, R.H., Martínez-Ruiz, C., 2008. The influence of aspect on the early
1003 growth dynamics of hydroseeded species in coal reclamation areas. *Appl. Veg. Sci.* 11,
1004 405–412. <https://doi.org/10.3170/2008-7-18497>
- 1005 Gorai, B., Jana, R.K., Premchand, 2003. Characteristics and utilisation of copper slag - A review.
1006 *Resour. Conserv. Recycl.* 39, 299–313. [https://doi.org/10.1016/S0921-3449\(02\)00171-4](https://doi.org/10.1016/S0921-3449(02)00171-4)
- 1007 Gou, M., Zhou, L., Then, N.W.Y., 2019. Utilization of tailings in cement and concrete: A review.
1008 *Sci. Eng. Compos. Mater.* 26, 449–464. <https://doi.org/10.1515/secm-2019-0029>
- 1009 Grabas, K., Pawlik, A., 2017. Wytrzymałość powłoki bitumicznej zabezpieczającej pylenie
1010 składowiska odpadów flotacyjnych “Żelazny Most.” *Górnictwo Odkryw.* 29–35.
- 1011 Grudinsky, P.I., Podjelnikova, E.S., Dyubanov, V.G., 2020. Research on the Process of
1012 Sulphatizing Roasting of Copper Slag Flotation Tailings Using Iron Sulphates. *IOP Conf.*
1013 *Ser. Earth Environ. Sci.* 459. <https://doi.org/10.1088/1755-1315/459/4/042004>
- 1014 Guo, Z., Feng, Q., Wang, W., Huang, Y., Deng, J., Xu, Z., 2016. Study on Flotation Tailings of
1015 Kaolinite-type Pyrite when Used as Cement Admixture and Concrete Admixture. *Procedia*
1016 *Environ. Sci.* 31, 644–652. <https://doi.org/10.1016/j.proenv.2016.02.118>
- 1017 Gupta, T., Ghosh, T., Akdogan, G., Bandopadhyay, S., 2017. Maximizing REE enrichment by
1018 froth flotation using Box-Behnken design in Alaskan coal. *SME Annu. Conf. Expo 2017*
1019 *Creat. Value a Cyclical Environ.* 408–412.
- 1020 Haines, P.W., Pietsch, B.A., Rawlings, D.J., Madigan, T.L., Findhammer, T.L., 1993. Mount
1021 Young 1:250 000 geological map series explanatory notes SD53-15. *North. Territ. Geol.*
1022 *Surv.* 1, 81.
- 1023 Henne, A., Craw, D., Vasconcelos, P., Southam, G., 2018. Bioleaching of waste material from
1024 the Salobo mine, Brazil: Recovery of refractory copper from Cu hosted in silicate minerals.
1025 *Chem. Geol.* 498, 72–82. <https://doi.org/10.1016/j.chemgeo.2018.08.029>
- 1026 Höller, W., Gandhi, S.M., 1997. Origin of tourmaline and oxide minerals from the
1027 metamorphosed Rampura Agucha Zn-Pb-(Ag) deposit, Rajasthan, India. *Mineral. Petrol.*
1028 60, 99–119. <https://doi.org/10.1007/bf01163137>



- 1029 Hossiney, N., Das, P., Mohan, M.K., George, J., 2018. In-plant production of bricks containing
1030 waste foundry sand—A study with Belgaum foundry industry. *Case Stud. Constr. Mater.*
1031 9, e00170. <https://doi.org/10.1016/j.cscm.2018.e00170>
- 1032 Hsi-chi, L., K'ai-wen, P., Ch'eng-fan, Y., Chien-ming, T., 1968. Copper-bearing sandstone (shale)
1033 deposits in yunnan. *Int. Geol. Rev.* 10, 870–882.
1034 <https://doi.org/10.1080/00206816809474948>
- 1035 Hu, G., Liu, H., Rana, A., Li, J., Bikass, S., Hewage, K., Sadiq, R., 2021. Life cycle assessment of
1036 low-temperature thermal desorption-based technologies for drill cuttings treatment. *J.*
1037 *Hazard. Mater.* 401, 123865. <https://doi.org/10.1016/j.jhazmat.2020.123865>
- 1038 Huang, C., Shi, Y., Gamal El-Din, M., Liu, Y., 2015. Treatment of oil sands process-affected
1039 water (OSPW) using ozonation combined with integrated fixed-film activated sludge
1040 (IFAS). *Water Res.* 85, 167–176. <https://doi.org/10.1016/j.watres.2015.08.019>
- 1041 Huang, J., Ren, T., Zou, H., 2019. Genesis of Xinzhai Sandstone-Type Copper Deposit in
1042 Northern Laos: Geological and Geotechnical Evidences. *J. Earth Sci.* 30, 95–108.
- 1043 Huang, Z., Xu, Z., Quan, Y., Jia, H., Li, J., Li, Q., Chen, Z., Pu, K., 2018. A review of treatment
1044 methods for oil-based drill cuttings. *IOP Conf. Ser. Earth Environ. Sci.* 170.
1045 <https://doi.org/10.1088/1755-1315/170/2/022074>
- 1046 Hudson-Edwards, K.A., Jamieson, H.E., Lottermoser, B.G., 2011. Mine wastes: Past, present,
1047 future. *Elements* 7, 375–380. <https://doi.org/10.2113/gselements.7.6.375>
- 1048 Hughes, B.D. & T.L.L., 1990. How to design a coal-bed methane well. *Pet. Eng. Int.* 5, 16–20.
- 1049 Hussain, I., Clapper, D., Doostdar, N., Hughes, B., 2017. Safe , Green Approach in Drill Cuttings
1050 Waste Mangement. *Soc. Pet. Eng.* 13–16.
- 1051 Informator Metale Nieżelazne [WWW Document], 2005. URL <https://metale.pl/wiedza/miedz>
1052 (accessed 1.14.21).
- 1053 Ismail, A.R., Alias, A.H., Sulaiman, W.R.W., Jaafar, M.Z., Ismail, I., 2017. Drilling fluid waste
1054 management in drilling for oil and gas wells. *Chem. Eng. Trans.* 56, 1351–1356.
1055 <https://doi.org/10.3303/CET1756226>
- 1056 Ismail, A.R., Rosli, W., Sulaiman, W., Jaafar, M.Z., 2015. Acute Toxicities of Drilling Fluids
1057 towards Guppy Fishes and Ghost Shrimp. *Aust. J. Basic Appl. Sci.* 150–154.
- 1058 Jakovljević, K., Mišljenović, T., Savović, J., Ranković, D., Ranđelović, D., Mihailović, N.,
1059 Jovanović, S., 2020. Accumulation of trace elements in Tussilago farfara colonizing post-
1060 flotation tailing sites in Serbia. *Environ. Sci. Pollut. Res.* 27, 4089–4103.
1061 <https://doi.org/10.1007/s11356-019-07010-z>
- 1062 Jarosiński, A., Madejska, L., 2008. Kompleksowe wykorzystanie surowców powstałych w
1063 wyniku procesu pozyskiwania koncentratów cynku. *Gospod. Surowcami Miner.* 24, 105–
1064 116.
- 1065 Jarosiński, A., Żelazny, S., Nowak, A.K., 2007. Warunki Otrzymywania Spoiwa Gipsowego Z
1066 Produktu Odpadowego Pochodzącego Z Procesu Pozyskiwania Koncentratu Cynku. *Czas.*
1067 *Tech. Ch* 1.

- 1068 Jin, Z., Li, Y.H., Zhao, C.L., Wang, J.X., 2013. Coal petrology and facies of No.6 coal of the
1069 Haerwusu Mine, Jungar Coalfield, Inner Mongolia. *J. Coal Sci. Eng.* 19, 295–302.
1070 <https://doi.org/10.1007/s12404-013-0305-2>
- 1071 João, L.C., Fernando, A.T., Poline, F.F., Geilma, L.V., Jamilla, E.S.L.T., 2017. Characterization of
1072 pre-treated drill cutting waste and its use as fine aggregate in concrete. *African J. Environ.*
1073 *Sci. Technol.* 11, 461–470. <https://doi.org/10.5897/ajest2015.1910>
- 1074 Karamanov, A., Aloisi, M., Pelino, M., 2007. Vitrification of copper flotation waste. *J. Hazard.*
1075 *Mater.* 140, 333–339. <https://doi.org/10.1016/j.jhazmat.2006.09.040>
- 1076 Karczewska, A., Kaszubkiewicz, J., Kabała, C., Jezierski, P., Spiak, Z., Szopka, K., 2017. Tailings
1077 Impoundments of Polish Copper Mining Industry-Environmental Effects, Risk Assessment
1078 and Reclamation, Assessment, Restoration and Reclamation of Mining Influenced Soils.
1079 Elsevier Inc. <https://doi.org/10.1016/B978-0-12-809588-1.00006-2>
- 1080 Kasowska, D., Gediga, K., Spiak, Z., 2018. Heavy metal and nutrient uptake in plants colonizing
1081 post-flotation copper tailings. *Environ. Sci. Pollut. Res.* 25, 824–835.
1082 <https://doi.org/10.1007/s11356-017-0451-y>
- 1083 KGHM, 2020. Pokłady możliwości Wyniki Grupy KGHM Polska Miedź.
- 1084 Kibort, K., Małachowska, A., 2018. Charakterystyka i właściwości kerogenu w kontekście
1085 wzbogacania rud miedzi 24–37.
- 1086 Kiventerä, J., Perumal, P., Yliniemi, J., Illikainen, M., 2020. Mine tailings as a raw material in
1087 alkali activation: A review. *Int. J. Miner. Metall. Mater.* 27, 1009–1020.
1088 <https://doi.org/10.1007/s12613-020-2129-6>
- 1089 Kołodziejczyk, A., 2019. Substancje groźne, niebezpieczne i pożyteczne.
- 1090 Konopacka, Ż., Zagożdżon, K.D., 2014. Łupek Miedzionośny Legnicko-Głogowskiego Okręgu
1091 Miedziowego. Łupek miedzionośny, WGGG PWr 7–12.
- 1092 Kopacz, M., 2015. Ocena kosztów gospodarki skałą płonną w funkcji zmiennego poziomu
1093 współczynnika uzysku węgla netto na przykładzie kopalni węgla kamiennego. *Gospod.*
1094 *Surowcami Miner. / Miner. Resour. Manag.* 31, 121–144. [https://doi.org/10.1515/gospo-](https://doi.org/10.1515/gospo-2015-28)
1095 [2015-28](https://doi.org/10.1515/gospo-2015-28)
- 1096 Köse, E.T., 2019. Drying of drill cuttings: Emphasis on energy consumption and thermal
1097 analysis. *Processes* 7. <https://doi.org/10.3390/pr7030145>
- 1098 Kotarska, I., 2012. Mining Waste from Copper Industry in Poland – Balance, Management and
1099 Environmental Aspects Key (In Polish: Odpady wydobywcze z górnictwa miedzi w Polsce -
1100 bilans, stan zagospodarowania i aspekty środowiskowe). *Cuprum* 65, 45–64.
- 1101 Kotarska, I., Mizera, B., Stefanek, P., 2018. Mining Waste in the Circular Economy - Idea Versus
1102 Reality. *E3S Web Conf.* 41, 1–7. <https://doi.org/10.1051/e3sconf/20184102013>
- 1103 Kotwica, L., Chorembala, M., Kapeluszná, E., Stepien, P., Deja, J., Illikainen, M., Golek, L., 2018.
1104 Influence of calcined mine tailings on the properties of alkali activated slag mortars. *Key*
1105 *Eng. Mater.* 761 KEM, 83–86. <https://doi.org/10.4028/www.scientific.net/KEM.761.83>
- 1106 Kowalczyk, W., 2019. Pokłady możliwości Rola innowacji w KGHM.

- 1107 Koziół, W., Uberman, R., 1996. Możliwości i warunki zagospodarowania odpadów z górnictwa
1108 i energetyki w drogownictwie, zwłaszcza do budowy autostrad i dróg ekspresowych.
1109 *Przegląd Geol.* 44, 701–709.
- 1110 Kudełko, J., 2018. Effectiveness of mineral waste management. *Int. J. Mining, Reclam. Environ.*
1111 32, 440–448. <https://doi.org/10.1080/17480930.2018.1438036>
- 1112 Kujawska, J., Pawłowska, M., 2020. Effect of drill cuttings addition on physicochemical and
1113 chemical properties of soil and red clover (*Trifolium pretense* L.) growth. *PLoS One* 15, 1–
1114 16. <https://doi.org/10.1371/journal.pone.0242081>
- 1115 Kujawska, J., Pawłowska, M., Wójcik, K., Baran, S., Żukowska, G., Pawłowski, A., 2016.
1116 Zastosowanie odpadów wydobywczych i kompostu z odpadów komunalnych do
1117 tworzenia materiałów glebopodobnych do rekultywacji terenów zdegradowanych. *Rocz.*
1118 *Ochr. Środowiska* Tom 18, cz.
- 1119 Kumar, R., 2013. Hyperspectral Data Analysis for Mineral mapping around Rampura Agucha
1120 Hyperspectral Data Analysis for Mineral mapping around Rampura Agucha and Pur
1121 Banera area , Rajasthan Submitted by Rohit Kumar Under supervision of Indian Institute
1122 of Remote Sensing In. <https://doi.org/10.13140/RG.2.2.21568.02561>
- 1123 Kyzas, G.Z., Matis, K.A., 2019. The flotation process can go green. *Processes* 7, 1–14.
1124 <https://doi.org/10.3390/pr7030138>
- 1125 Laing, T., 2020. The economic impact of the Coronavirus 2019 (Covid-2019): Implications for
1126 the mining industry. *Extr. Ind. Soc.* 7, 580–582.
1127 <https://doi.org/10.1016/j.exis.2020.04.003>
- 1128 Larachi, N., Bali, A., Ould Hamou, M., Bensaadi, S., 2019. Recovery of lead and barite from the
1129 abandoned Ichmoul mine wastes in Algeria. *Environ. Earth Sci.* 78, 1–12.
1130 <https://doi.org/10.1007/s12665-019-8593-5>
- 1131 Lazutkina, O.R., Buler, P.I., 2003. High-temperature protective properties of glass-enamel
1132 coatings based on coal ash. *Glas. Ceram. (English Transl. Steklo i Keramika)* 60, 185–186.
1133 <https://doi.org/10.1023/A:1025729521601>
- 1134 Leonard, S.A., Stegemann, J.A., 2010. Stabilization/solidification of petroleum drill cuttings. *J.*
1135 *Hazard. Mater.* 174, 463–472. <https://doi.org/10.1016/j.jhazmat.2009.09.075>
- 1136 Li, H., Zhang, W., Wang, J., Yang, Z., Li, L., Shih, K., 2018. Copper slag as a catalyst for mercury
1137 oxidation in coal combustion flue gas. *Waste Manag.* 74, 253–259.
1138 <https://doi.org/10.1016/j.wasman.2017.11.044>
- 1139 Lidelöw, S., Mácsik, J., Carabante, I., Kumpiene, J., 2017. Leaching behaviour of copper slag,
1140 construction and demolition waste and crushed rock used in a full-scale road
1141 construction. *J. Environ. Manage.* 204, 695–703.
1142 <https://doi.org/10.1016/j.jenvman.2017.09.032>
- 1143 Lin, S., Liu, R., Wu, M., Hu, Y., Sun, W., Shi, Z., Han, H., Li, W., 2020. Minimizing beneficiation
1144 wastewater through internal reuse of process water in flotation circuit. *J. Clean. Prod.*
1145 245, 118898. <https://doi.org/10.1016/j.jclepro.2019.118898>
- 1146 Liu, D.G., Min, X.B., Ke, Y., Chai, L.Y., Liang, Y. jie, Li, Y.C., Yao, L.W., Wang, Z.B., 2018. Co-

- 1147 treatment of flotation waste, neutralization sludge, and arsenic-containing gypsum
 1148 sludge from copper smelting: solidification/stabilization of arsenic and heavy metals with
 1149 minimal cement clinker. *Environ. Sci. Pollut. Res.* 25, 7600–7607.
 1150 <https://doi.org/10.1007/s11356-017-1084-x>
- 1151 Liu, H., Wang, W., Zhao, Y., Song, S., 2017. The water resistance of cement mortars prepared
 1152 with reverse flotation tailings. *Mag. Concr. Res.* 69, 966–972.
 1153 <https://doi.org/10.1680/jmacr.17.00021>
- 1154 Liu, S., Zhang, Y., Su, Z., Lu, M., Gu, F., Liu, J., Jiang, T., 2020. Recycling the domestic copper
 1155 scrap to address the China's copper sustainability. *J. Mater. Res. Technol.* 9, 2846–2855.
 1156 <https://doi.org/10.1016/j.jmrt.2020.01.019>
- 1157 Loganathan, K., Chelme-Ayala, P., Gamal El-Din, M., 2015. Effects of different pretreatments
 1158 on the performance of ceramic ultrafiltration membrane during the treatment of oil
 1159 sands tailings pond recycle water: A pilot-scale study. *J. Environ. Manage.* 151, 540–549.
 1160 <https://doi.org/10.1016/j.jenvman.2015.01.014>
- 1161 Longarini, N., Crespi, P.G., Zucca, M., Giordano, N., Silvestro, G., 2014. The advantages of fly
 1162 ash use in concrete structures. *Inz. Miner.* 15, 141–145.
- 1163 López, L., Ristorcelli, S., 2011. Technical Report for the Sierra Gorda Project, Chile.
- 1164 Łuszczkiewicz, A., 2000. Konceptcje wykorzystania odpadów flotacyjnych z przeróbki rud
 1165 miedzi w regionie legnicko-głogowskim. *Inżynieria Miner. R.* 1, nr 1, 25–35.
- 1166 Lutyński, A., Szpyrka, J., 2010. Zagospodarowanie drobnodziarnistych odpadów ze wzbogacania
 1167 węgla kamiennego. *Górnictwo i Geoinżynieria* 155–164.
- 1168 Mackay, I., Videla, A.R., Brito-Parada, P.R., 2020. The link between particle size and froth
 1169 stability - Implications for reprocessing of flotation tailings. *J. Clean. Prod.* 242, 118436.
 1170 <https://doi.org/10.1016/j.jclepro.2019.118436>
- 1171 Maghfouri-Moghadam, I., Zarei-Sahamieh, R., Ahmadi-Khalaji, A., Tahmasbi, Z., 2009.
 1172 Microbiostratigraphy of the Tarbur Formation, Zagros Basin, Iran. *J. Appl. Sci.* 9, 1781–
 1173 1785. <https://doi.org/10.3923/jas.2009.1781.1785>
- 1174 Maghfouri, S., Hosseinzadeh, M.R., Rajabi, A., Choulet, F., 2018. A review of major non-sulfide
 1175 zinc deposits in Iran, *Geoscience Frontiers*. Elsevier B.V.
 1176 <https://doi.org/10.1016/j.gsf.2017.04.003>
- 1177 Maiti, D., Pandey, V.C., 2020. Metal remediation potential of naturally occurring plants
 1178 growing on barren fly ash dumps. *Environ. Geochem. Health* 0123456789.
 1179 <https://doi.org/10.1007/s10653-020-00679-z>
- 1180 Mann, P., Gahagan, L., Gordon, M.B., 2005. Tectonic setting of the world's giant oil and gas
 1181 fields. *AAPG Mem.* 15–105. <https://doi.org/10.1306/m78834c2>
- 1182 Matlakowska, R., Włodarczyk, A., Słominska, B., Skłodowska, A., 2014. Extracellular elements-
 1183 mobilizing compounds produced by consortium of indigenous bacteria isolated from
 1184 Kupferschiefer black shale - implication for metals biorecovery from neutral and alkaline
 1185 polymetallic ores. *Physicochem. Probl. Miner. Process.* 50, 87–96.
 1186 <https://doi.org/10.5277/ppmp140108>

- 1187 Meggyes, T., Niederleithinger, E., Witt, K.J., Csövari, M., Kreft-Burman, K., Engels, J.,
 1188 Mcdonald, C., Roehl, K.E., 2008. Enhancing the safety of tailings management facilities.
 1189 Soil Sediment Contam. 17, 323–345. <https://doi.org/10.1080/15320380802143922>
- 1190 Melo, F., Laskowski, J.S., 2006. Fundamental properties of flotation frothers and their effect
 1191 on flotation. Miner. Eng. 19, 766–773. <https://doi.org/10.1016/j.mineng.2005.09.031>
- 1192 Mendez, M.O., Maier, R.M., 2008. Phytostabilization of mine tailings in arid and semiarid
 1193 environments - An emerging remediation technology. Environ. Health Perspect. 116,
 1194 278–283. <https://doi.org/10.1289/ehp.10608>
- 1195 Mikula, K., Izydorczyk, G., Skrzypczak, D., Moustakas, K., Witek-Krowiak, A., Chojnacka, K.,
 1196 2021. Value-added strategies for the sustainable handling, disposal, or value-added use
 1197 of copper smelter and refinery wastes. J. Hazard. Mater. 403, 123602.
 1198 <https://doi.org/10.1016/j.jhazmat.2020.123602>
- 1199 Mleczek, M., Rutkowski, P., Niedzielski, P., Goliński, P., Gąsecka, M., Kozubik, T., Dąbrowski, J.,
 1200 Budzyńska, S., Pakuła, J., 2016. The role of selected tree species in industrial sewage
 1201 sludge/flotation tailing management. Int. J. Phytoremediation 18, 1086–1095.
 1202 <https://doi.org/10.1080/15226514.2016.1183579>
- 1203 Moore, K.R., Whyte, N., Roberts, D., Allwood, J., Leal-Ayala, D.R., Bertrand, G., Bloodworth,
 1204 A.J., 2020. The re-direction of small deposit mining: Technological solutions for raw
 1205 materials supply security in a whole systems context. Resour. Conserv. Recycl. X 7,
 1206 100040. <https://doi.org/10.1016/j.rcrx.2020.100040>
- 1207 Muleya, F., Mulenga, B., Zulu, S.L., Nwaubani, S., Tembo, C.K., Mushota, H., 2020. Investigating
 1208 the suitability and cost-benefit of copper tailings as partial replacement of sand in
 1209 concrete in Zambia: an exploratory study. J. Eng. Des. Technol.
 1210 <https://doi.org/10.1108/JEDT-05-2020-0186>
- 1211 Muravyov, M.I., Fomchenko, N. V., 2018. Biohydrometallurgical treatment of old flotation
 1212 tailings of sulfide ores containing non-ferrous metals and gold. Miner. Eng. 122, 267–
 1213 276. <https://doi.org/10.1016/j.mineng.2018.04.007>
- 1214 Muravyov, M.I., Fomchenko, N. V., Usoltsev, A. V., Vasilyev, E.A., Kondrat'eva, T.F., 2012.
 1215 Leaching of copper and zinc from copper converter slag flotation tailings using H₂SO₄
 1216 and biologically generated Fe₂(SO₄)₃. Hydrometallurgy 119, 40–46.
 1217 <https://doi.org/10.1016/j.hydromet.2012.03.001>
- 1218 Muthusamy, K., Rasid, M.H., Jokhio, G.A., Mokhtar Albshir Budiea, A., Hussin, M.W., Mirza, J.,
 1219 2020. Coal bottom ash as sand replacement in concrete: A review. Constr. Build. Mater.
 1220 236, 117507. <https://doi.org/10.1016/j.conbuildmat.2019.117507>
- 1221 Mymrin, V., Correia, R.A.M., Alekseev, K., Klitzke, W., Avanci, M.A., Rolim, P.H.B., Argenta,
 1222 M.A., Carmo, J.B., 2020. Sustainable materials from hazardous lead ore flotation waste
 1223 in composites with spent foundry sand and clay. Int. J. Adv. Manuf. Technol. 109, 1333–
 1224 1344. <https://doi.org/10.1007/s00170-020-05722-y>
- 1225 Namkane, K., Naksata, W., Thiansem, S., Sooksamiti, P., Arqueropanyo, O. anong, 2017.
 1226 Utilization of leonardite and coal bottom ash for production of ceramic floor tiles.
 1227 Environ. Earth Sci. 76, 1–12. <https://doi.org/10.1007/s12665-017-6905-1>

- 1228 Nariyan, E., Sillanpää, M., Wolkersdorfer, C., 2017. Electrocoagulation treatment of mine
1229 water from the deepest working European metal mine – Performance, isotherm and
1230 kinetic studies. *Sep. Purif. Technol.* 177, 363–373.
1231 <https://doi.org/10.1016/j.seppur.2016.12.042>
- 1232 Natural gas production [WWW Document], 2019. URL
1233 [https://yearbook.enerdata.net/natural-gas/world-natural-gas-production-](https://yearbook.enerdata.net/natural-gas/world-natural-gas-production-statistics.html)
1234 [statistics.html](https://yearbook.enerdata.net/natural-gas/world-natural-gas-production-statistics.html) (accessed 1.14.21).
- 1235 Nieć, M., Salamon, E., Auguścik, J., 2018. Zmiany i zużycie zasobów złóż rud cynku i ołowiu w
1236 Polsce 129–152.
- 1237 Nikolić, I.P., Milošević, I.M., Milijić, N.N., Mihajlović, I.N., 2019. Cleaner production and
1238 technical effectiveness: Multi-criteria analysis of copper smelting facilities. *J. Clean. Prod.*
1239 215, 423–432. <https://doi.org/10.1016/j.jclepro.2019.01.109>
- 1240 Nowak, A.K., 2008. Ekologiczno - techniczne aspekty procesów pozyskiwania koncentratów
1241 cynku i ołowiu. *Rozpr. doktorska*.
- 1242 Nyga-Łukaszewska, H., Aruga, K., 2020. Energy Prices and COVID-Immunity: The Case of Crude
1243 Oil and Natural Gas Prices in the US and Japan. *Energies* 13, 1–32.
- 1244 Onuaguluchi, O., Eren, Ö., 2012. Recycling of copper tailings as an additive in cement mortars.
1245 *Constr. Build. Mater.* 37, 723–727. <https://doi.org/10.1016/j.conbuildmat.2012.08.009>
- 1246 Pacholewska, M., Cabała, J., Cwalina, B., Sozańska, M., 2007. Środowiskowe uwarunkowania
1247 procesów (bio)ługowania metali z odpadów poflotacyjnych rud cynkowo-ołowiowych.
1248 *Rudy i Met. niezależne* 337–342.
- 1249 Page, R.W., Jackson, M.J., Krassay, A.A., 2000. Constraining sequence stratigraphy in north
1250 Australian basins: SHRIMP U–Pb zircon geochronology between Mt Isa and McArthur
1251 River. *Aust. J. Earth Sci.* <https://doi.org/10.1046/j.1440-0952.2000.00797.x>
- 1252 Paiva, H., Yliniemi, J., Illikainen, M., Rocha, F., Ferreira, V.M., 2019. Mine tailings geopolymers
1253 as a waste management solution for a more sustainable habitat. *Sustain.* 11.
1254 <https://doi.org/10.3390/su11040995>
- 1255 Parbhakar-Fox, A., Glen, J., Raimondo, B., 2018. A geometallurgical approach to tailings
1256 management: An example from the savage river Fe-ore mine, western Tasmania.
1257 *Minerals* 8. <https://doi.org/10.3390/MIN8100454>
- 1258 Pavlovich, L.B., Alekseeva, N.M., Dolgoplov, V.P., Popov, A.A., 2004. Anti-corrosion paint and
1259 varnish coatings employing wastes from coke and coal chemicals production.
1260 *Metallurgist* 48, 272–274. <https://doi.org/10.1023/B:MELL.0000042826.03250.18>
- 1261 Pereira, L.B., Sad, C.M.S., da Silva, M., Corona, R.R.B., dos Santos, F.D., Gonçalves, G.R., Castro,
1262 E.V.R., Filgueiras, P.R., Lacerda, V., 2019. Oil recovery from water-based drilling fluid
1263 waste. *Fuel* 237, 335–343. <https://doi.org/10.1016/j.fuel.2018.10.007>
- 1264 Permata, E., McBride, S., 2010. Regulatory challenges of drill cuttings waste management in
1265 Indonesia. *Soc. Pet. Eng. - SPE Int. Conf. Heal. Saf. Environ. Oil Gas Explor. Prod.* 2010 2,
1266 1232–1236. <https://doi.org/10.2523/126738-ms>
- 1267 Pieczonka, J., Piestrzynski, A., Zygo, W., 2017. Złoże Cu-Mo Sierra Gorda, północne Chile. *Biul.*

- 1268 - Panstw. Inst. Geol. 469, 229–249. <https://doi.org/10.5604/01.3001.0010.0083>
- 1269 Pietrzykowski, M., Woś, B., Pająk, M., Likus-Cieślik, J., 2018. Assessment of tree vitality,
1270 biomass and morphology of Scots pine (*Pinus sylvestris* L.) root systems growing on
1271 reclaimed landfill waste after zinc and lead flotation. *For. Res. Pap.* 78, 323–331.
1272 <https://doi.org/10.1515/frp-2017-0036>
- 1273 PIG-PIB, 2020. Bilans perspektywicznych zasobów kopalin polski.
- 1274 Piszcz-Karaś, K., Klein, M., Hupka, J., Łuczak, J., 2019. Utilization of shale cuttings in production
1275 of lightweight aggregates. *J. Environ. Manage.* 231, 232–240.
1276 <https://doi.org/10.1016/j.jenvman.2018.09.101>
- 1277 Piwowarski, W., Żeglicki, J., 1977. Characteristics of deposits in the Bytom region. *Pr. Inst. Geol*
1278 19–44.
- 1279 Przeróbka kopalin miedziowych, 2008. . *J. Polish Miner. Eng. Soc.*
- 1280 Qiu, G., Luo, Z., Shi, Z., Ni, M., 2011. Utilization of coal gangue and copper tailings as clay for
1281 cement clinker calcinations. *J. Wuhan Univ. Technol. Mater. Sci. Ed.* 26, 1205–1210.
1282 <https://doi.org/10.1007/s11595-011-0391-1>
- 1283 Rad, S.A.M., Modarres, A., 2017. Durability properties of non-air entrained roller compacted
1284 concrete pavement containing coal waste ash in presence of de-icing salts. *Cold Reg. Sci.*
1285 *Technol.* 137, 48–59. <https://doi.org/10.1016/j.coldregions.2017.02.006>
- 1286 Radić, R., Milošević, Jurić, S., Čudić, S., 2016. Flotation of ores and waste waters. *Metalurgija*
1287 55, 832–834.
- 1288 Rahman, M.T., Mohajerani, A., Giustozzi, F., 2020. Recycling of waste materials for asphalt
1289 concrete and bitumen: A review. *Materials (Basel)*. 13.
1290 <https://doi.org/10.3390/ma13071495>
- 1291 Rajczyk, K., 2017. Mineral binder obtained by burning of flotation wastes from copper ore in
1292 KGHM POLSKA MIEDŹ S.A. *Cem. Wapno Bet.* 239–248.
- 1293 Rani, R., Jain, M.K., 2017. Effect of bottom ash at different ratios on hydraulic transportation
1294 of fly ash during mine fill. *Powder Technol.* 315, 309–317.
1295 <https://doi.org/10.1016/j.powtec.2017.04.025>
- 1296 Retka, J., Rzepa, G., Bajda, T., Drewniak, L., 2020. The use of mining waste materials for the
1297 treatment of acid and alkaline mine wastewater. *Minerals* 10, 1–22.
1298 <https://doi.org/10.3390/min10121061>
- 1299 Reuben, N.O., Perez, P.A., Josiah, M.A., Abdul, M.M., 2018. Towards enhancing sustainable
1300 reuse of pre-treated drill cuttings for construction purposes by near-infrared analysis: A
1301 review. *J. Civ. Eng. Constr. Technol.* 9, 19–39. <https://doi.org/10.5897/jcct2018.0482>
- 1302 Ristić, N., Grdić, Z., Ćurčić, G.T., Grdić, D., Krstić, D., 2019. Properties of self-compacting
1303 concrete produced with waste materials as mineral admixture. *Rev. Rom. Mater. Rom. J.*
1304 *Mater.* 49, 568–580.
- 1305 Ristorcelli, S., Ronning, P., Fahey, P. and Lustig, G., 2008. Updated Technical Report on the
1306 Sierra Gorda Project, Region II, Chile.

- 1307 Robbins, C.A., Graubeger, B.M., Garland, S.D., Carlson, K.H., Lin, S., Bandhauer, T.M., Tong,
1308 T., 2020. On-site treatment capacity of membrane distillation powered by waste heat or
1309 natural gas for unconventional oil and gas wastewater in the Denver-Julesburg Basin.
1310 Environ. Int. 145, 106142. <https://doi.org/10.1016/j.envint.2020.106142>
- 1311 Romero-García, A., Iglesias-González, N., Romero, R., Lorenzo-Tallafigo, J., Mazuelos, A.,
1312 Carranza, F., 2019. Valorisation of a flotation tailing by bioleaching and brine leaching,
1313 fostering environmental protection and sustainable development. J. Clean. Prod. 233,
1314 573–581. <https://doi.org/10.1016/j.jclepro.2019.06.118>
- 1315 Romero, F.M., Armienta, M.A., González-Hernández, G., 2007. Solid-phase control on the
1316 mobility of potentially toxic elements in an abandoned lead/zinc mine tailings
1317 impoundment, Taxco, Mexico. Appl. Geochemistry 22, 109–127.
1318 <https://doi.org/10.1016/j.apgeochem.2006.07.017>
- 1319 Rossetti, P., Dino, G.A., Biglia, G., Costa, E., 2019. Characterization of Secondary Raw Materials
1320 From Mine Waste : a Case Study From the Campello Monti Ni ± Cu ± Co ± Pge Mining Site
1321 (Western Alps , Italy).
- 1322 Rubio, J., Souza, M.L., Smith, R.W., 2002. Overview of flotation as a wastewater treatment
1323 technique. Miner. Eng. 15, 139–155.
- 1324 Rykusova, N., Shestopalov, O., Shchukina, L., Briankin, O., Galushka, Y., 2020. Study of the
1325 Properties of Drill Cuttings At Their Use As Technogenic Raw Materials for the Production
1326 of Building Ceramics. ScienceRise 1, 10–22. <https://doi.org/10.21303/sr.v0i1.1158>
- 1327 Shengo, L., Mutiti, W., 2016. Bio-treatment and water reuse as feasible treatment approaches
1328 for improving wastewater management during flotation of copper ores. Int. J. Environ.
1329 Sci. Technol. 13, 2505–2520. <https://doi.org/10.1007/s13762-016-1073-5>
- 1330 Sikora, S., Wojna-Dyląg Elżbieta, 2010. Zagrożenia środowiska występujące podczas
1331 eksploatacji podmorskich złóż węglowodorów. Wiert. Naft. Gaz 369–379.
- 1332 Śliwka, M., Baran, A., Wieczorek, J., 2013. Evaluation of toxic metal bioaccumulation in a
1333 reservoir of flotation tailings. Polish J. Environ. Stud. 22, 909–914.
- 1334 Śliwka, M., Kępyś, W., Pawul, M., 2019. Evaluation of the possibility of using post-production
1335 waste from Zn-Pb ores as a material for natural land reclamation. Rocz. Ochr. Sr. 21,
1336 1343–1365.
- 1337 Song, Y., Yang, C., Wei, S., Yang, H., Fang, X., Lu, H., 2018. Tectonic control, reconstruction and
1338 preservation of the tiegelongnan porphyry and epithermal overprinting Cu (Au) deposit,
1339 central Tibet, China. Minerals 8, 1–17. <https://doi.org/10.3390/min8090398>
- 1340 Stanojlović, R.D., Sokolović, J.M., 2014. A study of the optimal model of the flotation kinetics
1341 of copper slag from copper mine BOR. Arch. Min. Sci. 59, 821–834.
1342 <https://doi.org/10.2478/amsc-2014-0057>
- 1343 Steliga, T., Uliasz, M., 2012. Wybrane zagadnienia środowiskowe podczas poszukiwania ,
1344 udostępniania i eksploatacji gazu ziemnego z formacji łupkowych. NAFTA-GAZ 5, 273–
1345 283.
- 1346 Stuckman, M., Edenborn, H.M., Lopano, C., Alexandra Hakala, J., 2018. Advanced

- 1347 characterization and novel waste management for drill cuttings from Marcellus shale
1348 energy development. SPE/AAPG/SEG Unconv. Resour. Technol. Conf. 2018, URTC 2018
1349 1–10. <https://doi.org/10.15530/urtec-2018-2883168>
- 1350 Sua-iam, G., Makul, N., Cheng, S., Sokrai, P., 2019. Workability and compressive strength
1351 development of self-consolidating concrete incorporating rice husk ash and foundry sand
1352 waste – A preliminary experimental study. *Constr. Build. Mater.* 228, 116813.
1353 <https://doi.org/10.1016/j.conbuildmat.2019.116813>
- 1354 Tumidajski, T., Łuszczkiewicz, A., Drzymala, J., Trybalski, K., Foszcz, D., Muszer, A., Henc, T.,
1355 2008. Określenie wpływu wzbogacalności przerabianych rud na jakość koncentratów
1356 miedziowych dla potrzeba optymalizacji górnictwo-hutniczego procesu wytwarzania
1357 miedzi. Kraków.
- 1358 Unearthing Australia's toxic coal ash legacy, 2019.
- 1359 Van der Graaf, 2018. [https://www.researchgate.net/post/Why-zinc-and-lead-are-usually-](https://www.researchgate.net/post/Why-zinc-and-lead-are-usually-related-in-carbonates-deposits#similar)
1360 [related-in-carbonates-deposits#similar](https://www.researchgate.net/post/Why-zinc-and-lead-are-usually-related-in-carbonates-deposits#similar) [WWW Document].
- 1361 Wang, W., Liu, D., Tu, Y., Jin, L., Wang, H., 2020. Enrichment of residual carbon in entrained-
1362 flow gasification coal fine slag by ultrasonic flotation. *Fuel* 278.
1363 <https://doi.org/10.1016/j.fuel.2020.118195>
- 1364 Wang, W., Zhao, Y., Liu, H., Song, S., 2017. Fabrication and mechanism of cement-based
1365 waterproof material using silicate tailings from reverse flotation. *Powder Technol.* 315,
1366 422–429. <https://doi.org/10.1016/j.powtec.2017.04.029>
- 1367 Wei, Y.C., Peng, Y., 2015. Effect of froth stability on dewatering of coal flotation concentrates.
1368 *Trans. Institutions Min. Metall. Sect. C Miner. Process. Extr. Metall.* 124, 167–174.
1369 <https://doi.org/10.1179/1743285515Y.0000000007>
- 1370 Woynarowska, A., Żelazny, S., Żukowski, W., 2011. Oczyszczanie ścieków powstających w
1371 procesie otrzymywania koncentratów cynku i ołowiu za pomocą wymiennicy jonowych.
1372 *Nauk. Przyr. Technol.*
- 1373 Woźniak, J., Pactwa, K., 2018. Overview of polish mining wastes with circular economy model
1374 and its comparison with other wastes. *Sustain.* 10. <https://doi.org/10.3390/su10113994>
- 1375 Yagüe, S., Sánchez, I., De La Villa, R.V., García-Giménez, R., Zapardiel, A., Frías, M., 2018. Coal-
1376 mining tailings as a pozzolanic material in cements industry. *Minerals* 8, 1–13.
1377 <https://doi.org/10.3390/min8020046>
- 1378 Yi, R.R., Cao, W., 2014. Current situation and prospect of comprehensive utilization of red
1379 mud. *Appl. Mech. Mater.* 522–524, 811–816.
1380 <https://doi.org/10.4028/www.scientific.net/AMM.522-524.811>
- 1381 Yin, S., Shao, Y., Wu, A., Wang, H., Liu, X., Wang, Y., 2020. A systematic review of paste
1382 technology in metal mines for cleaner production in China. *J. Clean. Prod.* 247.
1383 <https://doi.org/10.1016/j.jclepro.2019.119590>
- 1384 Yu, Q., Nagataki, S., Lin, J., Saeki, T., Hisada, M., 2005. The leachability of heavy metals in
1385 hardened fly ash cement and cement-solidified fly ash. *Cem. Concr. Res.* 35, 1056–1063.
1386 <https://doi.org/10.1016/j.cemconres.2004.03.031>

- 1387 Zanoletti, A., Cornelio, A., Bontempi, E., 2021. A post-pandemic sustainable scenario: What
1388 actions can be pursued to increase the raw materials availability? *Environ. Res.* 202,
1389 111681. <https://doi.org/10.1016/j.envres.2021.111681>
- 1390 Zheng, K., Zhou, J., Gbozee, M., 2015. Influences of phosphate tailings on hydration and
1391 properties of Portland cement. *Constr. Build. Mater.* 98, 593–601.
1392 <https://doi.org/10.1016/j.conbuildmat.2015.08.115>
- 1393 Zhou, H., Bhattarai, R., Li, Y., Li, S., Fan, Y., 2019. Utilization of coal fly and bottom ash pellet
1394 for phosphorus adsorption: Sustainable management and evaluation. *Resour. Conserv.*
1395 *Recycl.* 149, 372–380. <https://doi.org/10.1016/j.resconrec.2019.06.017>
- 1396